



Bonneagar Iompair Éireann
Transport Infrastructure Ireland

TII Publications



Notes for Guidance on the Specification for Road Works Series NG 2600 - Miscellaneous

CC-GSW-02600

December 2010

About TII

Transport Infrastructure Ireland (TII) is responsible for managing and improving the country's national road and light rail networks.

About TII Publications

TII maintains an online suite of technical publications, which is managed through the TII Publications website. The contents of TII Publications is clearly split into 'Standards' and 'Technical' documentation. All documentation for implementation on TII schemes is collectively referred to as TII Publications (Standards), and all other documentation within the system is collectively referred to as TII Publications (Technical). This system replaces the NRA Design Manual for Roads and Bridges (NRA DMRB) and the NRA Manual of Contract Documents for Road Works (NRA MCDRW).

Document Attributes

Each document within TII Publications has a range of attributes associated with it, which allows for efficient access and retrieval of the document from the website. These attributes are also contained on the inside cover of each current document, for reference. For migration of documents from the NRA and RPA to the new system, each current document was assigned with new outer front and rear covers. Apart from the covers, and inside cover pages, the documents contain the same information as previously within the NRA or RPA systems, including historical references such as those contained within NRA DMRB and NRA MCDRW.

Document Attributes

TII Publication Title	<i>Notes for Guidance on the Specification for Road Works Series NG 2600 - Miscellaneous</i>
TII Publication Number	<i>CC-GSW-02600</i>

Activity	<i>Construction & Commissioning (CC)</i>
Stream	<i>Guidance on Specification for Works (GSW)</i>
Document Number	<i>02600</i>

Document Set	<i>Standards</i>
Publication Date	<i>December 2010</i>
Historical Reference	<i>Series NG 2600</i>

NRA DMRB and MCDRW References

For all documents that existed within the NRA DMRB or the NRA MCDRW prior to the launch of TII Publications, the NRA document reference used previously is listed above under 'historical reference'. The TII Publication Number also shown above now supersedes this historical reference. All historical references within this document are deemed to be replaced by the TII Publication Number. For the equivalent TII Publication Number for all other historical references contained within this document, please refer to the TII Publications website.

MISCELLANEOUS

Contents

<i>Clause</i>	<i>Title</i>	<i>Page</i>
NG 2601	Bedding Mortar.....	2
NG 2602	Concrete for Ancillary Purposes	2
NG	Sample Appendices.....	4

Miscellaneous

NG 2601 Bedding Mortar

General

- 1 Great importance is attached to the material having flow characteristics sufficient for it to occupy all the spaces between base plates and the surrounding sub-strata completely, including around all holding down bolts. The Specification for Road Works does not cover non-flowing mortars or dry pack mortars.

Where a higher strength is required, this should be specified in Appendix 26/2. Materials with higher strengths may be more temperature sensitive and variable.

Mortar test cubes required in connection with early loading should be cured under conditions which simulate as far as possible those of the mortar in the Works.

Materials

- 2 (i) The minimum thickness of bedding mortar should be 10 mm and the maximum thickness without reinforcement should be 30 mm. This will allow sufficient space to enable filling yet reduce creep and shrinkage effects. The nominal thickness, with tolerances, should be shown on the drawings in the Contract.
(ii) A purpose-made portable insulated store, equipped with thermostatically controlled heaters, would be suitable for complying with sub-Clause 2601.2(ii)(a). It may be convenient to include provision for storage of the mixing water at 20°C.

Site Mixing, Placing and Curing

- 3 (i) It is common practice to add the dry material to the water in the mixer. If the material does not flow correctly the addition of extra water or dry mortar to the sample is not permissible. In order to control the amount of water accurately it is good practice to use a proprietary graduated container. A bucket with a mark is not suitable.
(ii) Where permanent shims are used underneath base plates to align or support parapet posts etc. they should take the form of either central packers or slotted washers placed around the shanks of the holding down bolts. Packers and washers should be made of materials

which will not corrode. Adequate bedding cover should also be provided to the packers and washers to ensure that they are fully protected from the weather and any road and traffic contaminants. Packers and washers should be compatible with the materials used in the base plates or bolts.

- (iii) Addition of mortar may be required to form a finished plinth. Voids may occur under the base plate if this operation is carried out incorrectly.
- (iv) The quantity of mortar in the plinth extending beyond the base plate should be kept to a minimum to reduce cracking. Forming of large plinths to support two or more base plates is not recommended.

Approval Tests

- 4 (i) It is important that the various temperatures required in the flow tests are accurately maintained within the tolerances specified. The testing laboratory appointed should be able to demonstrate that it has the facilities for accurate cold testing.
(ii) Where different methods of placing the mortar are proposed, e.g. pumping, or where the geometry of the base plate is significantly different from that shown on Highways Agency Highway Construction Detail (HCD) Drawing No. K2, then the glass plate test, specified in sub-Clause 2601.4(iii), should be modified.

Batch Acceptance Tests

- 5 The tests on Site should be conducted by a competent person. Proof of ability to carry out the flow cone test method consistently may be checked by trials using water.

NG 2602 Concrete for Ancillary Purposes

- 1 Concrete mixes complying with Clause 2602 will normally be suitable for the purposes described in Table 26/3 and need not be shown on the drawings in the Contract for these purposes. Standardized prescribed mixes from IS EN 206-1 may also be suitable for other purposes and should be called up on drawings in the Contract where necessary. Sub-Clause 1 of Clause 2602 makes it unnecessary to do more than show "ST4 concrete" (for example) on the drawings in the Contract. The relationship between concrete mix and

strength of the concrete is given in Annex NB of IS EN 206-1.

- 2 Where additional requirements are necessary, for example the use of sulfate-resisting cement in ground containing sulfates (see Table F1 of Annex F to IS EN 206-1), or resistance to alkali-silica reaction, these requirements should be specified in Appendix 26/1. Air entrainment will not normally be necessary but if it is required, this should also be specified in Appendix 26/1. Alkali-silica reaction will not normally be a risk because

cement contents are comparatively low but in some areas where aggregates are known to be highly reactive, it may be necessary to state in Appendix 26/1 that ancillary concrete is to comply with sub-Clause 1704.5 for ST4 Standardized prescribed mix.

- 3 Foundations for traffic sign supports and lighting columns should, where necessary, be structural concrete complying with the 1700 Series and be shown on the drawings in the Contract accordingly.

NG Sample Appendices

NG SAMPLE APPENDIX 26/1: CONCRETE FOR ANCILLARY PURPOSES

[Note to compiler: Special requirements for Concrete for Ancillary Purposes, e.g. sulphate-resisting cement, nominal maximum aggregate size, requirements for surface finishes etc. should be listed here. Also to distinguish different mix designs, mix references should be listed here but differentiated from those for structural concrete in Appendix 17/1]

NG SAMPLE APPENDIX 26/2: BEDDING MORTAR

[Note to compiler: Include here:]

- 1 Compressive strength and flow characteristic requirements. *[Where different from 2601.1(I & (ii))]*
- 2 Maximum stress in the mortar *[2601]*.
- 2 Locations at which permanent metal shims are acceptable *[2601.3 (v)]*.
- 3 Early loading requirements [For bridge bearings, cross-reference should be made to Appendix 21/1].

NG SAMPLE APPENDIX 26/3: CORED THERMOPLASTIC NODE MARKERS

[Note to compiler: Include here:]

- 1 Locations of node markers *[2606.1]*.
- 2 Copies of existing site records.
- 3 References for the re-establishment of existing node markers.



Bonneagar Iompair Éireann
Transport Infrastructure Ireland



Ionad Ghnó Gheata na
Páirce,

Stráid Gheata na Páirce,
Baile Átha Cliath 8, Éire



Parkgate Business Centre,
Parkgate Street,
Dublin 8, Ireland



www.tii.ie



+353 (01) 646 3600



info@tii.ie



+353 (01) 646 3601