



DOUBLE SURFACE DRESSING –

10mm CRUSHED ROCK CHIPPINGS AT RATE OF 9–12 kg/m<sup>2</sup>  
AND CATIONIC BITUMEN EMULSION AT RATE OF 1.3 TO 1.6 l/m<sup>2</sup>

ON

14mm CRUSHED ROCK CHIPPINGS AT RATE OF 12–15 kg/m<sup>2</sup>  
AND CATIONIC BITUMEN EMULSION AT RATE OF 1.2 TO 1.6 l/m<sup>2</sup>

NOTES :

1. CENTRE OF ACCESS ROAD TO BE 150mm ABOVE EXISTING GROUND LEVEL.