



Bonneagar Iompair Éireann
Transport Infrastructure Ireland

TII Publications



Specification for Road Works Series 1000 - Road Pavements - Concrete Materials

CC-SPW-01000

March 2013

About TII

Transport Infrastructure Ireland (TII) is responsible for managing and improving the country's national road and light rail networks.

About TII Publications

TII maintains an online suite of technical publications, which is managed through the TII Publications website. The contents of TII Publications is clearly split into 'Standards' and 'Technical' documentation. All documentation for implementation on TII schemes is collectively referred to as TII Publications (Standards), and all other documentation within the system is collectively referred to as TII Publications (Technical). This system replaces the NRA Design Manual for Roads and Bridges (NRA DMRB) and the NRA Manual of Contract Documents for Road Works (NRA MCDRW).

Document Attributes

Each document within TII Publications has a range of attributes associated with it, which allows for efficient access and retrieval of the document from the website. These attributes are also contained on the inside cover of each current document, for reference. For migration of documents from the NRA and RPA to the new system, each current document was assigned with new outer front and rear covers. Apart from the covers, and inside cover pages, the documents contain the same information as previously within the NRA or RPA systems, including historical references such as those contained within NRA DMRB and NRA MCDRW.

Document Attributes

TII Publication Title	<i>Specification for Road Works Series 1000 - Road Pavements - Concrete Materials</i>
TII Publication Number	<i>CC-SPW-01000</i>

Activity	<i>Construction & Commissioning (CC)</i>
Stream	<i>Specification for Works (SPW)</i>
Document Number	<i>01000</i>

Document Set	<i>Standards</i>
Publication Date	<i>March 2013</i>
Historical Reference	<i>Series 1000</i>

NRA DMRB and MCDRW References

For all documents that existed within the NRA DMRB or the NRA MCDRW prior to the launch of TII Publications, the NRA document reference used previously is listed above under 'historical reference'. The TII Publication Number also shown above now supersedes this historical reference. All historical references within this document are deemed to be replaced by the TII Publication Number. For the equivalent TII Publication Number for all other historical references contained within this document, please refer to the TII Publications website.

ROAD PAVEMENTS – CONCRETE MATERIALS

Contents

<i>Clause</i>	<i>Title</i>	<i>Page</i>
1001	Strength Classes of Concrete and Constituent Materials for Pavement Layers	1
1002	Air Content	3
1003	Density	4
1004	Pavement Concrete Strength.....	4
1005	Consistence (Workability)	6
1006	Not Used.....	6
1007	Separation and Waterproof Membranes	6
1008	Steel Reinforcement.....	6
1009	Transverse Joints	8
1010	Longitudinal Joints	10
1011	Dowel Bars	10
1012	Tie Bars	12
1013	Joint Grooves	13
1014	Groove Formers and Bottom Crack Inducers.....	15
1015	Joint Filler Board.....	15
1016	Preparation and Sealing of Joint Grooves.....	17
1017	Joint Seals.....	20
1018	Joints at Manhole and Gully Slabs	21
1019	Inspection of Dowel Bars	22
1020	Side Forms, Rails and Guide Wires	22
1021	Not Used.....	23
1022	Not Used.....	23
1023	Transport and Delivery	23
1024	Construction by Machine	23
1025	Construction by Small Paving Machines or Hand Guided Methods	26
1026	Finished Surface Requirements.....	27
1027	Curing	28

1028	Trial Length	29
1029	Texturing of Hardened Concrete	30
1030	Not Used.....	31
1031	Measurement of Macrotexture Depth – Volumetric patch Technique	31
1032	Thin Bonded Repairs	31
1033	Full Depth Repairs and Reinstatements.....	32
1034	Summary of Rates for Sampling and Testing Concrete for Pavement Layers	36
1035 to 1042	Not Used	36
1043	Foamed Concrete.....	36
1044	Pavements with an Exposed Aggregate Concrete Surface.....	38
1045	Weather Conditions for Laying of Cementitious Materials	42
1046 to 1047	Not Used	42
1048	Use of Surfaces by Traffic and Construction Plant.....	42

ROAD PAVEMENTS - CONCRETE MATERIALS

1001 Strength Classes of Concrete and Constituent Materials for Pavement Layers

- 1 Concrete in rigid or rigid composite pavements shall be one of the classes given in Table 10/1, in accordance with the pavement design alternatives permitted in Appendix 7/1. The use of Unreinforced Concrete (URC) or Jointed Reinforced Concrete (JRC) in pavements on National Roads requires a Departure from Standard from the National Roads Authority.
- 2 Unless otherwise specified in Appendix 7/1 concrete shall conform to the requirements of IS EN 13877-2 and the requirements of this Series. The constituents of the concrete shall conform to IS EN 206-1 and IS EN 13877-1 and the requirements of this Series.

Cement

- 3 'Cement' in this Series shall be as defined in Irish National Annex to IS EN 206-1 (Tables NA 2 and NA 3) and shall comprise one of the following:
 - (i) Cements:
 - (a) Portland cement CEM I;
 - (b) Portland-slag cement CEM II/A-S and CEM II/B-S;
 - (c) Blastfurnace cement CEM III/A;
 - (d) Portland-fly ash cement CEM II/A-V;
 - (e) Portland limestone cements CEM II/A-L and CEM II/A-LL.
 - (ii) Combinations with a Type II addition (see Irish National Annex to IS EN 206-1 Clause NA 2.4 and NA 2.7) shall comprise one of the following:
 - (a) CEM II/A-L(LL) or CEM II/A-V cement conforming to I.S. EN 197-1 with addition of ggbs conforming to IS EN 15167-1 up to a maximum of 50% by weight (expressed as ggbs/(cement+ggbs)), provided that equivalent strength performance is demonstrated to at least a class 42,5N cement;
 - (B) CEM I, CEM II/A-L(LL) or CEM II/A-V cement conforming to I.S. EN 197-1 with addition of Fly Ash conforming to I.S. EN 450-1 in accordance with the requirements of Clause NA 2.7 of the Irish National Annex to I.S. EN 206-1.
 - (iii) In each cubic metre of fully compacted concrete the cement content shall be in accordance with Table 10/2. For 20mm maximum size aggregate add 20kg/m³, and for < 20mm maximum size add 40kg/m³.
 - (iv) When used, the proportion of silica fume to CEM I shall be 10 ± 1%.

Water

- 4 Water from a water company supply may be used without testing. Water from other sources may be used if it conforms to IS EN 1008. The water content shall be the minimum required to provide the specified consistence for full compaction of the concrete to the required density, as determined by trial concrete mixes or other means, and the maximum free water/cement ratio shall be 0,45 for strength classes CC37, CC28, C32/40 and C25/30.

TABLE 10/1: Pavement Layers - Concrete Strength Classes

Pavement Layer	IS EN 13877-2	IS EN 206-1, IS EN 13877-1	Clause
(i) Surface slabs; Unreinforced Concrete (URC) Jointed Reinforced concrete (JRC) Continuously Reinforced concrete pavement (CRCP)	1. CC37	2. C32/40) 1001 to) 1034 and) 1044
(ii) Continuously reinforced concrete base (CRCB)	3. CC37	4. C32/40	5.))
(iii) CRCP and CRCB ground beam anchorages	6. *	7. C25/30	8.)

NOTE: * Cores shall not be taken from ground beam anchorages

TABLE 10/2: Minimum Cement or Combination Contents with 40 mm Maximum Aggregate

Class (IS EN 206-1)	C32/40	C32/40	C25/30
Class (IS EN 13877-2)	CC37	CC37	CC28
Cement	In Surface Slabs overlaid by Bituminous Materials	In at least the top 50mm of surface slabs	
Min. Portland cement CEM I IS EN 197-1 (kg/m ³)	320	320	280
Min. other cements or combinations permitted in sub-Clauses 3(i) and 3(ii) (kg/m ³)	340	340	300
Maximum proportion of ggbs (%)	50	35	65
Max/Min proportion of pfa(%)	35/15	25/15	35/15
Min. CEM I content (kg/m ³)	220	255	200

NOTES: (a) denotes maximum aggregate/cement ratio of 14:1 by mass.
(b) denotes maximum aggregate/cement ratio of 18:1 by mass.

Admixtures

- 5 Concrete in at least the top 50mm of surface slabs shall incorporate an air-entraining admixture complying with IS EN 934-2, except:
- (i) for pavements with an exposed aggregate concrete surface constructed to Clause 1044 where at least the top 40mm of the surface slab shall be air entrained;
- Or
- (ii) for surface slabs of pavements with at least a class C40/50 concrete;
 - (iii) for surface slabs of pavements with a class C32/40 concrete which are to be overlaid by a 30mm minimum thickness PMSMA complying with Clause 942.
 - (iv) Plasticisers or water reducing admixtures shall comply with IS EN 934-2. Admixtures containing calcium chloride shall not be used.

Aggregate

- 6 Aggregates for all pavement concrete shall be natural material, excluding flint, and complying with IS EN 12620.
- 7 The flakiness index of the coarse aggregate when determined by the method described in I.S. EN 933-3 shall not exceed FI_{35} except when natural, uncrushed aggregates are used for concrete of strength classes lower than C32/40, when the flakiness index shall not exceed FI_{50} .
- 8 Once the appropriate gradings have been determined they shall not be varied without the approval of the Employer's Representative.
- 9 The water absorption (WA) of the coarse aggregate from the source determined in accordance with IS EN 1097-2 shall also be declared.
- 10 The maximum size of coarse aggregate (D) shall not exceed 40 mm. When the spacing between longitudinal reinforcement is less than 90 mm, the maximum size of coarse aggregate (D) shall not exceed 20 mm.
- 11 Sand (i.e. fine aggregate) containing more than 25% by mass of acid-soluble material as determined in accordance with IS EN 196-2 and BRE Special Digest 1, Part 2, Appendix 3, in either the fraction retained on, or the fraction passing the 0.500 mm sieve, shall not be used in the top 50 mm of surface slabs. This requirement will not apply for pavements with an exposed aggregate concrete surface constructed to Clause 1044 or if it can be shown that the sand (i.e. fine aggregate) retained on, or the fraction passing the 0.500 mm sieve, contains less than 25 percent by weight of calcium carbonate.

Chloride Content

- 12 The chloride ion content of the aggregate to be used in concrete with embedded metal shall be determined in accordance with the Volhard reference method in IS EN 1744-1 and shall be as stated in IS EN 206-1. The chloride class of reinforced concrete or concrete containing embedded metal shall be class Cl 0,40 and unreinforced concrete shall be class Cl 1,0.

Chemical Requirement

- 13 The acid-soluble sulphate content of the aggregates and filler aggregates for concrete pavements shall comply with IS EN 12620, clause 6.3.1 and shall be Category AS_{0,2}.

1002 Air Content

- 1 The concrete shall meet the requirement for exposure class XF4 in IS EN 206-1. This shall be achieved by the use of an air-entraining agent. The minimum quantity of air in air-entrained concrete as a percentage of the volume of the concrete shall be as in Table 10/3:

Table 10/3: Minimum air contents

Maximum aggregate size (mm)	Minimum air content (%)
20	9. 3,5
10. 40	11. 3

- 2 The air content shall be determined at the point of delivery to the paving plant by the pressure gauge method in accordance with IS EN 12350-7, at the rate of one determination per 300m² of slab or at least 6 times per day, whichever is the greater, in conjunction with tests for consistence and strength. For areas less than 300m² the rate shall be at least one determination to each 20m length of slab or less constructed at any one time or at least 3 times per day. If the air content is outside the specified limits in IS EN 206-1 the Contractor shall remove the concrete from the Works.
- 3 The air-entraining agent shall be added at the mixer, by an apparatus capable of dispensing the correct dose within the tolerance for admixtures given in IS EN 206-1, to ensure uniform distribution of the agent throughout the batch during mixing.

1003 Density

- 1 The density of a saturated core cut from the full depth of the concrete pavement shall not be less than 95% of the average density of at least six fully compacted saturated moulded specimens made from the same concrete and tested at the same age.
- 2 The density of the concrete pavement shall be determined in accordance with IS EN 13877-2. The density of a saturated core cut from the full depth of the concrete pavement shall be determined in accordance with IS EN 12390-7. The determination of the saturated density of the fully compacted moulded specimens shall be in accordance with IS EN 12350-1, IS EN 12390-1 and IS EN 12390-2.
- 3 The core shall have an average diameter of at least four times the nominal maximum aggregate size, and in any case at least 100mm diameter. Where different concrete mixes are used in separate layers, the density of each layer shall be separately determined by splitting or cutting the cores between the layers.
- 4 Cores shall be taken at the rate given in Clause 1028 for trial bays and according to Category 2 in Table 7 of IS EN 13877-2 for the main slab. If the density of any core is below the minimum required, the concrete across the whole width of the slab constructed at the time relating to that core shall be removed. In unreinforced concrete the whole slab length between joints shall be removed. For reinforced slabs, in order to determine the limit of the defective area of concrete which shall be removed, additional cores shall be taken at 5m intervals on each side of any defective core until concrete of satisfactory density is found. Defective areas shall be made good with new material in accordance with the Specification.
- 5 In calculating the density, allowance shall be made for any steel in the cores.
- 6 Core holes shall be reinstated with compacted concrete with mix proportions of 1 part of Portland cement CEM I: 2 parts of sand: 2 parts of 10mm single sized coarse aggregate by mass.

1004 Pavement Concrete Strength

- 1 Sampling and testing for, and compliance with the specified characteristic core strength of designed concretes shall be undertaken by compressive strength testing in accordance with IS EN 13877-2 on cores cut from the full depth of the slab. The modification to compressive strength results of cores not tested at a maturity of 28 days at 20 °C which is described in IS EN 13877-2 shall not be used.

- 2 Concrete cores of the appropriate size shall be taken, cured and tested in accordance with IS EN 12504-1 with the exception that the core shall be cured under water at 20°C ±2°C from as soon as practically possible. The sampling rate shall be as designated in IS EN 13877-2 for Category 2, three cores shall be taken from areas of concrete of up to 3000m² and one additional core for every further 1000m² of concrete laid.
- 3 An exception to the above sampling rate is that in the trial slab at least six cores shall be taken, three to be tested at 7 days and three at 28 days.
- 4 The end preparation of the core shall be by grinding and the height/diameter (h/d) ratio of the tested specimen shall be between 1 and 2.
- 5 If during the construction of the trial length the average corrected core compressive strength, from the three cores, falls below the 7 day corrected core compressive strength given in Table 10/4. Then either the cement content of the concrete shall be increased by 5% by mass, or, a further trial slab shall be constructed using an improved compaction technique and/or an increased cement content. The increased cement content shall be maintained at least until the three corresponding 28-day core strength tests have been assessed. If the cement content is increased, the concrete shall be adjusted to maintain the required consistence.

TABLE 10/4: 7 Day Corrected Core Compressive Strengths

Class of Concrete	CEM I concretes N/mm ²	CEM 1 with pfa or ggbs concretes N/mm ²
CC37	32	26,5
CC28	25	20
CC18.5	16,5	13
CC14	12	10
CC9	7,5	6,5
CC7	5	4

- 6 Overlapping groups of four consecutive 28 day corrected core strengths shall be used for assessing the pavement for compliance with the criteria in Table A.1 of IS EN 13877-2. The pavement shall be accepted if both the criteria in Table A.1 are satisfied for four results derived from strength tests on cores taken from the constructed pavement. Conformity control of the concrete will be the responsibility of Contractor.
- 7 On small projects constructed to IS EN 13877-1 cubes shall be used for compliance.
- 8 To assess the time for use of a concrete slab by traffic, the strength development rate may be predetermined by cubes stored at 20°C made from trial concrete mixes and maturity meters placed in the pavement. Alternatively pairs of cubes may be made for each 600m² or less and stored alongside the pavement in containers or in such a way that their sides are well insulated. If thermal insulation is used for accelerated curing the cubes shall be similarly insulated. Pairs of cubes shall be tested at the intervals specified in Appendix 7/1. Tests for compliance with the specified strength shall be made in the normal way.

1005 Consistence (Workability)

- 1 The consistence shall be determined by the Degree of Compactibility (Compaction Index) test in accordance with IS EN 12350-4, or the Vebe test in accordance with IS EN 12350-3. The sampling for all concrete classes shall be undertaken in accordance with IS EN 12350-1 and the rate of testing in accordance with Table 12 of IS EN 206-1. Consistence shall be carried out at the point of placing, in conjunction with tests for strength and any tests for air content. The consistence shall be maintained at the optimum within the limits specified in IS EN 206-1.
- 2 If any determination of consistence gives a result outside the tolerance, a further test shall be made immediately on the next available load of concrete. The average of the two consecutive results and the difference between them shall be calculated. If the average is not within the tolerance or the difference is greater than 0,1 for CI or 6 seconds for Vebe, subsequent samples shall be taken from the delivery vehicles, which shall not be allowed to discharge into the Works until compliance with the Specification has been established.

1006 Not Used

1007 Separation and Waterproof Membranes

- 1 A separation membrane shall be used between jointed reinforced concrete surface slabs or unreinforced concrete surface slabs and the sub-base.
- 2 Separation membranes shall be impermeable plastic sheeting 125 microns thick laid flat without creases. Where an overlap of plastic sheets is necessary, this shall be at least 300 mm. There shall be no standing water on or under the membrane when the concrete is placed upon it.
- 3 Under CRCP and CRCB a waterproof membrane shall be provided, which shall be a bituminous spray in accordance with Clause 920 before concreting. Where a bituminous spray has been used to cure cement-bound material then only those areas, which have been damaged, shall be re-sprayed after making good.

1008 Steel Reinforcement

General

- 1 Reinforcement shall comply with any of the following standards and shall be cut and bent in accordance with BS 8666. The reinforcement materials shall be obtained from a firm holding a valid CARES (or fully equivalent scheme) certificate of approval. Re-bending of carbon steel bars and fabric reinforcement on site shall not be permitted:
 - Hot Rolled and Cold Worked Carbon Steel Bars
 - (i) IS EN 10080 and BS 4449 (Grade B500B or B500C).
 - Steel Wires
 - (ii) IS EN 10080 and BS 4482 (Ribbed Grade B500).
 - Steel Fabric
 - (iii) IS EN 10080 and BS 4483 (Grade B500A, B500B or B500C). Steel fabric reinforcement shall have a minimum nominal bar size of 6mm (8mm for Grade B500A). Steel fabric reinforcement shall be delivered to site in flat mats or pre-bent.

- 2 For hot rolled and cold worked carbon steel bars, and for steel fabric reinforcement, the bond property requirements for BS 4449 shall be complied with based on the surface geometry requirements of that standard. For steel wire, the bond property requirements of BS 4482 shall be complied with based on the surface geometry requirements of that standard.
- 3 Spacing of bars shall not be less than twice the maximum size of aggregate used. Laps in longitudinal bars shall be not less than 35 bar diameters or 450mm whichever is greater. In continuously reinforced concrete slabs (CRCP or CRCB), only one third of the laps may be in any one transverse section, except in single bay width construction where half the laps may be in any one transverse section. There shall be a minimum of 1,2m longitudinally between groups of transverse laps or laps in prefabricated reinforcement sheets. Alternatively the reinforcement may be butt welded in accordance with Clause 1717.
- 4 Laps in any transverse reinforcement shall be a minimum of 300mm. Where prefabricated reinforcement sheets are used and longitudinal and transverse laps would coincide, no lap is required in the transverse bars within the lap of the longitudinal reinforcement. These transverse bars may be cropped or fabricated shorter so that the requirements for cover are met. Alternatively, prefabricated sheets incorporating splices (i.e. flying ends) may be used to provide nesting of reinforcement in both directions at lap positions. The lengths of the laps shall be the minimum values previously stated.
- 5 If the reinforcement is positioned prior to concreting, it shall be fixed on supports and retained in position at the required depth below the finished surface and distance from the edge of the slab so as to ensure that the required cover is achieved. Reinforcement assembled on site shall be tied or firmly fixed, at sufficient intersections to provide sufficient rigidity to ensure that the reinforcement remains in the correct position during construction of the slab.
- 6 Alternatively, when a reinforced concrete slab (JRC, CRCP or CRCB) is constructed in two layers, the reinforcement in the form of prefabricated sheets may be placed on or into the bottom layer which shall be spread and compacted to such a level that it will support the reinforcement without distortion at the required position in the slab. The sheets shall be tied together at overlaps and after the second layer has been spread and compacted, the reinforcement shall have the required cover.
- 7 When a reinforced concrete slab is constructed at maximum width as in Clause 1010 the transverse reinforcement in the centre of each slab width shall be a minimum of 12mm nominal diameter bars at 600mm centres. This reinforcement shall be at least 600mm longer than one third of the width of the slab and be lapped to other transverse reinforcement bars or sheets, or be continuous across the whole width of each slab.

Jointed Reinforced Concrete Slabs

- 8 The reinforcement shall be so placed that after compaction of the concrete, the cover below the finished surface of the slab is 50 ± 10 mm for slabs less than 200mm thick, 60 ± 10 mm for slabs 200mm or more but less than 270mm thick, 70 ± 20 mm for slabs 270mm thick or more. The negative vertical tolerance shall not be permitted beneath road stud recesses. Where traffic signal detector loops are to be installed, the minimum cover to the reinforcement from the surface shall be 100mm. The vertical cover between any longitudinal joint groove forming strip and any reinforcement or tie bars shall be a minimum of 30mm. Any transverse bars shall be at right angles to the longitudinal axis of the carriageway. Any transverse reinforcement shall terminate at 125 ± 25 mm from the edges of the slab and longitudinal joints, where tie bars as in Clause 1012 are used. No longitudinal bars shall lie within 100mm of a longitudinal joint. The reinforcement shall terminate $300\text{mm} \pm 50\text{mm}$ from any transverse joint, excluding emergency construction joints.

Continuously Reinforced Concrete Slabs (CRCP or CRCB)

- 9** The reinforcement shall be Grade 460 deformed steel bars with the diameters and spacings as described in Appendix 7/1.
- 10** The reinforcement shall consist of bars assembled on site, or of prefabricated sheets. Except where otherwise shown on the drawings in the Contract the longitudinal bars shall be parallel to the centre-line of the road.
- 11** The reinforcement shall be positioned so that, after compaction of the concrete, it shall be at the mid depth of the specified thickness of the slab $\pm 25\text{mm}$. No longitudinal bar shall lie within 100mm of a longitudinal joint. In reinforcement assembled on site, longitudinal bars shall be placed immediately above any transverse bars, which shall be at right angles to the longitudinal axis of the carriageway. Any transverse reinforcement shall terminate $125 \pm 25\text{mm}$ from the edges of the slab and longitudinal joints where tie bars as in Clause 1012 are used.

1009 Transverse Joints

General

- 1** Transverse joints shall be provided in unreinforced and jointed reinforced concrete slabs and shall be contraction, expansion or warping joints at the spacings described in Appendix 7/1, such that for unreinforced concrete slabs the length/width ratio shall be not greater than 2,0. The spacings may be increased by 20% if limestone coarse aggregate is used throughout the depth of the slab.
- 2** Joints in the surface slab and sub-base shall be staggered so that they are not coincident vertically and are at least 1m apart.
- 3** Transverse joints shall be straight within the following tolerances along the intended line of the joint, which is the straight line transverse to the longitudinal axis of the carriageway, except at road junctions or roundabouts where the positions shall be as shown on the drawings in the Contract.
 - (i) deviations of the filler board or bottom crack inducer from the intended line of the joint shall be not greater than $\pm 10\text{mm}$;
 - (ii) the best fit straight line through the joint groove as constructed shall be not more than 25 mm from the intended line of the joint;
 - (iii) deviations of the joint groove from the best fit straight line of the joint shall be not greater than 10mm.
- 4** Transverse joints on each side of a longitudinal joint shall be in line with each other and of the same type and width. The position of the joints relative to manholes and gullies shall be in accordance with Clause 1018.
- 5** Concrete pavement layers shall be isolated from fixed structures by expansion joints, or earthworks or a granular layer over the structure, or by bridge-type expansion joints, or by lengths of fully flexible pavement construction. End of pavement surface slabs shall have a transition bay as shown on the drawings in the Contract, leading into the fully flexible construction.
- 6** Transverse joints shall have a sealing groove which shall be sealed in compliance with Clause 1016.

Contraction Joints

- 7 Contraction joints shall consist of:
- (i) a sawn joint groove complying with Clause 1013;
 - (ii) dowel bars complying with Clause 1011;
 - (iii) a sealing groove complying with Clause 1016.

Expansion Joints

- 8 Expansion joints shall consist of:
- (i) a joint filler board complying with Clause 1015;
 - (ii) dowel bars complying with Clause 1011;
 - (iii) a sealing groove complying with Clause 1016.
- 9 The filler board shall be positioned vertically within the prefabricated joint assemblies along the line of the joint within the tolerances given in sub-Clause 3 of this Clause, and at such depth below the surface as will not impede the passage of the finishing beams on the paving machines. The joint filler board together with the sealing groove shall provide a complete separation of adjacent slabs and any spaces around dowel bars and between the sub-base and the filler board shall be packed with a suitable compressible material after fixing the joint assembly.

Warping Joints

- 10 Warping joints shall consist of:
- (i) a sawn joint groove complying with Clause 1013;
 - (ii) tie bars complying with Clause 1012;
 - (iii) a sealing groove complying with Clause 1016.

Construction Joints

- 11 Construction joints made at the end of a working day in unreinforced concrete slabs and jointed reinforced concrete slabs shall be contraction joints. In the event of mechanical breakdown of the concreting machinery, or at the onset of adverse weather, emergency joints may be formed.
- 12 Emergency joints in unreinforced concrete slabs shall be contraction joints not less than 2,5m from the preceding or succeeding joint position.
- 13 Emergency joints in jointed reinforced concrete slabs shall be not less than 2,5m from the preceding or succeeding joint position. The stop end formwork shall be sufficiently rigid to ensure that dowel bars, tie bars or reinforcement will be held in position in compliance with the specification, and placed in such a position that it permits the longitudinal reinforcement to project through the joint for a distance of at least 750mm.
- 14 Construction joints in continuously reinforced concrete slabs (CRCP and CRCB) at end of day or in an emergency shall not be constructed within 1,5m of any lap in the longitudinal reinforcement. The stop end formwork shall be sufficiently rigid to ensure that the longitudinal reinforcement and the tie bars as required in sub-Clause 1012.7 which project through the joint are held in the correct position.

1010 Longitudinal Joints

General

- 1 Sawn or wet-formed longitudinal joints shall be provided in surface slabs between or at the centre of traffic lanes within the allowable positions as shown on the drawings in the Contract, so that bay widths are not greater than 4,2m (or 5,0m with limestone aggregate) for unreinforced slabs, or 6m (or 7,6m with limestone aggregate) for reinforced concrete surface slabs with transverse reinforcement as in sub-Clause 1008.7. Longitudinal joints shall be provided in CRCB between lanes or at the centre of lanes, within a tolerance of $\pm 150\text{mm}$ so that bay widths are not greater than 6m (or 7,6m with limestone aggregate). Joints in the surface slab, base or sub-base shall be staggered so that they are not coincident vertically and are at least 300mm apart.
- 2 Wet-formed longitudinal joints shall consist of wet-formed joint grooves complying with Clause 1013, a bottom crack inducer complying with Clause 1014 and tie bars complying with Clause 1012, except where transverse reinforcement is permitted in lieu.
- 3 Longitudinal joints shall be constructed within the following tolerances:
 - (i) deviations of the bottom crack inducer from the intended line of the joint, parallel to the axis of the road shall be not greater than $\pm 13\text{mm}$;
 - (ii) the joint groove shall be located vertically above the bottom crack inducers within a horizontal tolerance of $\pm 25\text{mm}$;
 - (iii) the best fit line along the constructed joint groove, shall be not more than 25mm from the intended line of the joint;
 - (iv) deviations of the joint groove from the best fit line of the joint shall be not greater than 10mm.
- 4 Sawn longitudinal joints shall consist of joint grooves complying with Clause 1013.
- 5 Tie bars may be replaced by continuous transverse reinforcement across the joints in continuously reinforced concrete slabs which are constructed in more than one lane width in one operation, provided that the transverse reinforcement is a minimum of 12mm diameter bars at 600mm centres. The transverse reinforcement in these circumstances shall be protected in accordance with sub-Clause 1012.2.

Longitudinal Construction Joints

- 6 Longitudinal construction joints between separate slabs shall have tie bars as in Clause 1012 with a joint groove as in Clause 1013. Alternatively, if split forms are used, the transverse reinforcement, if 12mm diameter or more, may be continued across the joint for a minimum of 500mm or 30 times the diameter of the transverse reinforcement bars, whichever is the greater. The transverse reinforcement in these circumstances shall be protected by suitable bituminous paint or equivalent coating for a distance of at least 75mm either side of the joint. A joint sealing groove is not required in construction joints in continuously reinforced concrete bases. Where the edge of the concrete slab is damaged it shall be made good before the adjacent slab is constructed.

1011 Dowel Bars

- 1 Dowel bars shall be Grade B500B steel conforming to IS EN 13877-3 and shall be free from oil, dirt, loose rust and scale. They shall be straight, free of burrs and other irregularities and the sliding ends sawn or cropped cleanly with no protrusions outside the normal diameter of the bar. For

- expansion joints, dowel bars shall be 25mm diameter at 300mm spacing and 600mm long for slabs up to 239mm thick and 32mm diameter for thicker slabs. For contraction joints, dowels shall be 20mm diameter at 300mm spacing and 400mm long for slabs up to 239mm thick, and 25mm diameter at 300mm spacing and 600mm long for thicker slabs.
- 2 Dowel bars shall be supported on cradles in prefabricated joint assemblies positioned prior to construction of the slab. For contraction joints, as an alternative to prefabricated assemblies, dowel bars may be mechanically inserted with vibration into the concrete by a method which ensures full re-compaction of the concrete around the dowel bars and the surface finished by a diagonal finishing beam, or a longitudinal oscillating float travelling across the slab.
 - 3 Dowel bars shall be positioned at mid-depth from the surface level of the slab ± 20 mm. They shall be aligned parallel to the finished surface of the slab, to the centre line of the carriageway and to each other within the following tolerances:
 - (i) for bars supported on cradles prior to construction of the slab and for inserted bars in two layer construction prior to placing the top layer:
 - (a) all bars in a joint shall be within ± 3 mm per 300mm length of bar;
two thirds of the bars shall be within ± 2 mm per 300mm length of bar;
no bar shall differ in alignment from an adjoining bar by more than 3mm per 300mm length of bar in either the horizontal or vertical plane;
 - (ii) for all bars, after construction of the slab:
 - (a) twice the tolerances for alignment as in (i) above;
equally positioned about the intended line of the joint within a tolerance of 25mm.
 - 4 Cradles supporting dowel bars shall not extend across the line of the joint.
 - 5 Dowel bars, supported on cradles in assemblies, when subjected to a load of 110N applied at either end and in either the vertical or horizontal direction (upwards and downwards and both directions horizontally) shall not deflect more than the following limits:
 - (i) two thirds of the number of bars of any assembly tested shall not deflect more than 2mm per 300mm length of bar;
 - (ii) the remainder of the bars in that assembly shall not deflect more than 3mm per 300mm length of bar.
 - 6 The assembly of dowel bars and supporting cradles, including the joint filler board in the case of expansion joints shall have the following degree of rigidity when fixed in position:
 - (i) For expansion joints the deflection of the top edge of the filler board shall be not greater than 13mm, when a load of 1,3kN is applied perpendicular to the vertical face of the joint filler board and distributed over a length of 600mm by means of a bar or timber packing, at mid depth and midway between individual fixings, or 300mm from either end of any length of filler board, if a continuous fixing is used. The residual deflection after removal of the load shall be not more than 3mm.
 - (ii) The joint assembly fixings to the sub-base shall not fail under the 1,3kN load applied for testing the rigidity of the assembly but shall fail before the load reaches 2,6kN.
 - (iii) The fixings for contraction joints shall not fail under a 1,3kN load and shall fail before the load reaches 2,6kN when applied over a length of 600mm by means of a bar or timber packing placed as near to the level of the line of fixings as practicable.

- (iv) Failure of the fixings shall be deemed to be when there is displacement of the assemblies by more than 3mm with any form of fixing, under the test load. The displacement shall be measured at the nearest part of the assembly to the centre of the bar or timber packing.
- 7 Dowel bars shall be covered by a flexible polymeric corrosion resistant coating, bonded onto the previously cleaned bar. The coating shall be smooth and free of indentations. During coating, the bar shall be supported at each end. Minimum thickness shall be 0,3mm. The coating shall also be able to withstand 250 hours immersion in a salt fog cabinet complying with IS EN ISO 7253, without showing any visible crazing or corrosion of the protected bar. The coated bar shall comply with the following pull out test:
- (i) Four bars shall be taken at random from stock and without any special preparation shall be coated as required in this Clause. The dowel bars which have been coated shall be cast centrally into concrete specimens 150 x 150 x 450mm, made of the same concrete mix proportions to be used in the pavement, but with a maximum aggregate size of 20mm and cured in accordance with IS EN 12390-2. At 7 days a tensile load shall be applied to achieve a movement of the bar of at least 0,25mm. The average bond stress to achieve this movement shall be not greater than 0,14 N/mm².
- 8 For expansion joints, a closely fitting cap 100mm long consisting of waterproofed cardboard or suitable synthetic material shall be placed over one end of each dowel bar. An expansion space 10mm greater than the thickness of the joint filler board shall be formed between the end of the cap and the end of the dowel bar.

1012 Tie Bars

- 1 Tie bars in transverse or longitudinal joints shall conform to Clause 1008, in accordance with the requirements given below and Table 10/5.
- 2 Tie bars for use across joints shall have corrosion protection in the form of a flexible polymeric corrosion resistant coating, bonded centrally onto 150mm of the previously cleaned centre section of the bars. Where tie bars are to be cranked for construction joints and later straightened, the coating shall be shown to be capable of being straightened through 90 degrees without cracking. The coating for both straight and cranked bars after straightening shall be able to withstand 250 hours immersion in a salt fog cabinet complying with IS EN ISO 9227, without showing any visible crazing or cracking, or corrosion of the protected part of the bar.
- 3 Tie bars in warping joints and wet-formed longitudinal joints shall be made up into rigid assemblies with adequate supports and fixings to remain firmly in position during the construction of the slab.
- 4 Alternatively, tie bars at longitudinal joints may be mechanically inserted by vibration from above using a method which ensures re-compaction of the concrete around the tie bars.
- 5 At longitudinal construction joints, tie bars may be adequately fixed to side forms or inserted into the side of the slab by a method which ensures re-compaction of the concrete around the tie bars and adequate bond.
- 6 Tie bars in warping joints shall be positioned from the top surface of the slab within +20, -10mm of the mid depth of the slab. Tie bars in other joints shall be positioned and remain within the middle third of the slab depth, approximately parallel to the surface and approximately perpendicular to the line of the joint, with the centre of each bar on the intended line of the joints within a tolerance of \pm 50mm, and with a minimum cover of 30mm below any top crack inducer of joint groove for slabs 200mm thick or more, or 20mm for slabs up to 200mm thick.

- 7 At transverse construction joints in continuously reinforced concrete, tie bars shall be 1,5m long and of the same Grade and size as the longitudinal reinforcement, and shall be fixed at twice the normal spacing midway between the longitudinal reinforcement bars so that $750\text{mm} \pm 50\text{mm}$ extends each side of the joint at the same level as the longitudinal reinforcement and shall be tied to the transverse reinforcement. Where paving from a construction joint is not resumed within 5 days, an extra longitudinal reinforcement bar 8m long shall be lapped and tied to each tie bar. These extra bars may be combined with the tie bars. Where the spacing between longitudinal reinforcement and the extra 8m long bars is less than 90mm, the nominal size of aggregate shall be 20mm for a sufficient number of concrete batches to complete that section of pavement.
- 8 Where tie bars are used in longitudinal joints in continuously reinforced concrete they shall be placed at the same level as the transverse reinforcement and tied to the longitudinal reinforcement.

1013 Joint Grooves

General

- 1 Transverse contraction or warping joint grooves shall be sawn in the hardened concrete.
- 2 Transverse joint grooves which are initially constructed less than the full width of the slab shall be completed by sawing through to the edge of the slab and across longitudinal joints as soon as any forms have been removed and before an induced crack develops at the joint.

Sawn Transverse and Longitudinal Joint Grooves

- 3 Sawing shall be undertaken as soon as possible after the concrete has hardened sufficiently to enable a sharp edged groove to be produced without disrupting the concrete and before random cracks develop in the slab. The grooves shall be between $1/4$ and $1/3$ of the specified depth of the slab and of any convenient width not less than 3 mm. The sealing groove may be sawn to the required width later. Expansion joint sealing grooves shall be sealed as soon as practical after sawing.

TABLE 10/5: Tie Bar Details

Joints	Diameter mm	Grade of Steel	Length mm	Spacing mm
Transverse construction joints in continuously reinforced concrete	As for main reinforcement	Grade B500B or B500C	1500	Twice the spacing of the reinforcement
Emergency construction joints in jointed reinforced concrete slabs other than at contraction or expansion joints	12	Grade B500B or B500C	1000	600
			750	600
Warping joints	12	Grade B500B or B500C	1000	300
			750	600
Longitudinal All joints except where Transverse reinforcement is permitted in lieu	12 Or 16 Or 20	Grade B500B or B500C Grade B500B or B500C Grade B500B or B500C	1000	600
			750	
			600	600
Transition from rigid to flexible construction	20	Grade B500B or B500C	1000	300

NOTE: The transverse reinforcement may be continued across the joint in reinforced concrete if the bars are of a minimum nominal diameter of 12mm and the bars are protected from corrosion and the cover is as required in this Clause.

Wet-formed Longitudinal Joint Grooves

- When slabs are constructed in more than one lane width in one operation a joint groove shall be formed by inserting a groove former ahead of the finishing beams from dispenser. The concrete so displaced shall be re-compacted by a vibrating compactor or similar device, at least 300mm wide operating symmetrically along the line of the joint. After finishing the concrete, the groove forming strip shall be in the correct position and alignment, within 10° of the vertical, and to sufficient depth below the surface to allow for the passage of the finishing beam within the range 0-3mm below the finished level of the slab. Groove forming strips in wet-formed longitudinal joint grooves shall be left in place.

Construction Joint Grooves in Surface Slabs

- The grooves shall be formed by fixing a groove-former or strip or cork seal along the top edge of the slab already constructed, before concreting the adjacent slab. Where the edge of the concrete is damaged it shall be ground or made good before fixing the groove forming strip. Alternatively the subsequent slab may be placed adjacent to the first and a sealing groove sawn later in the hardened concrete to the minimum depth required in Table 10/6 or to the manufacturer's instructions if greater, and to sufficient width to eliminate minor spalling of the joint arris, up to a maximum of 25mm for longitudinal joints and 40mm for transverse joints. The joint shall be sealed in compliance with Clause 1016.

1014 Groove Formers and Bottom Crack Inducers

General

- 1 Except where joint grooves are sawn, a bottom crack inducer shall be provided at each longitudinal joint position.
- 2 The bottom crack inducer shall be triangular or inverted Y-shaped fillet, with a base width not less than the height, made of timber or rigid synthetic material. It shall be firmly fixed to the sub-base so as to remain in position during the whole process of constructing the slab.
- 3 The combined depth of groove formers and bottom crack inducers shall be between 1/4 and 1/3 of the depth of the slab and the difference between the depth of the groove former and the height of the bottom crack inducer shall not be greater than 20mm.

Longitudinal Joints

- 4 Groove forming sealing strips for wet-formed longitudinal joints shall be of firm compressible strips of ethylene vinyl acetate foam of minimum density 90kg/m^3 , or synthetic rubber, or equivalent material. They shall have a minimum thickness of 5mm and shall be sufficiently rigid to remain vertical and straight in the concrete without curving or stretching. They shall be inserted continuously along the joint.

CRCP Universal Beam Anchorage Transverse Joint

- 5 One side of the beam shall be separated from the CRCP slab by an expansion joint filler board against the vertical face and ethylene vinyl acetate foam in accordance with HCD Drawing C20.

1015 Joint Filler Board

- 1 Joint filler board for expansion joints and manhole and gully slab joints shall be 25mm thick unless otherwise shown in the drawings in the Contract, within a tolerance of $\pm 1,5\text{mm}$. It shall be a self-expanding cork seal or a firm compressible material or a bonded combination of compressible and rigid materials of sufficient rigidity to resist deformation during the passage of the concrete paving plant. The depth of the joint filler board for manhole and gully slabs shall be the full depth of the slab less the depth of the sealing groove. In expansion joints, the filler board shall have a ridged top as shown on the drawings in the Contract, except where a sealing groove former is indicated on those drawings. Holes for dowel bars shall be accurately bored or punched out to form a sliding fit for the sheathed dowel bar.
- 2 The joint filler board shall meet the requirements given when tested in accordance with the procedures in the following sub-Clauses:
 - (i) Weathering Test
 - (a) Three specimens, each 115mm square $\pm 2,5\text{mm}$, shall be placed in a ventilated drying oven maintained at a temperature of $55^\circ\text{C} \pm 5^\circ\text{C}$ for 7 days, after which they shall immediately be immersed in water at room temperature of between 16°C and 21°C for 24 hours. They shall then be subjected to five cycles of freezing and thawing in the following manner.
 - (b) The specimens shall be placed in a watertight weathering test pan having a ribbed bottom and a fitted slotted lid designed to hold the three specimens vertically on edge. The pan shall be filled with water to half the depth of the specimens and then frozen to minus 7°C or below, for at least four hours after the initial freezing of the

water. The pan shall then be placed in a water bath maintained at 18°C to 38°C without disturbing the specimens and shall remain there for one hour after thawing has completed. The pan and specimens shall then be returned to the refrigerator and freezing and thawing shall be repeated in precisely the same manner until five cycles of the process have been completed. The specimens shall be removed from the pan and air dried at room temperature for 48 hours before examination.

- (c) The material shall be deemed to have passed the weathering test if the specimens show no signs of disintegration or shrinkage.

(ii) Compression and Recovery Test

- (a) Two of the specimens which pass the weathering test, and two new specimens, each trimmed to 100mm square \pm 0,5mm, maintained at room temperature and humidity for 24 hours, shall be subjected to three applications of load at 24 hour intervals in a compression test machine complying with IS EN ISO 7500-1, with auxiliary platens 100mm², minimum 13mm thick. During each application of load each specimen shall be compressed to 50% of its original thickness at a rate of strain of 1,3mm per minute. The load required to achieve this amount of compression shall be not less than 0,07N/mm² nor more than 10N/mm² for material to be used in pavements and not less than 0,07N/mm² and not more than 0,4N/mm² for material to be used in bridge joints. The load shall be released immediately the required degree of compression is reached and after the third application a recovery period of 30 minutes shall be allowed after which the thickness of the specimen shall be measured.
- (b) This thickness, expressed as a percentage of the original thickness, is the 'recovery' value of the specimen. The thicknesses shall be measured to an accuracy of 25 micron. The two new specimens shall be weighed before and after testing. The difference in mass shall be determined with an accuracy of 0,1% and shall be expressed as a percentage of the original mass of the specimen.
- (c) The material shall be deemed to have passed the test if all four specimens have recovery values of at least 70% and the two new specimens have not suffered a reduction of mass in excess of 1%.

(iii) Extrusion Test

- (a) The third sample which passes the weathering test shall be trimmed to 100mm square \pm 0,5mm and be subjected to the following extrusion test.
- (b) The extrusion mould shall be 100mm x 100mm (+ 0,5mm, - 0) internally, of sufficient depth to test the sample as received, open on one side only and fixed rigidly to a base plate. The mould shall be provided with a closely fitting pressure plate which shall fit without binding, and with an accurate horizontal measuring dial gauge or measuring device accurate to 25 microns. The specimen shall be mounted in the extrusion mould and loaded once as described in the compression and recovery test. The extrusion at the open side of the mould shall be measured with the gauge when the specimen is compressed to 50% of its original thickness and before release of the load.
- (c) The material shall be deemed to have passed the test if the extrusion of the free edge does not exceed 6mm.

(iv) Immersion Test for Cork Filler Board

- (a) Two specimens each 115mm x 115mm \pm 2,5mm shall be prepared and the thickness of each specimen shall be determined to the nearest 25 microns before the specimens are immersed in boiling water for one hour. After removal from the water

the specimens shall be allowed to cool to room temperature and after 15 minutes at this temperature their thickness shall be re-measured to the nearest 25 microns.

- (b) The material shall be deemed to have passed the test if both specimens have a thickness of not less than 140% of their thickness before immersion.
- (v) Acid Test for Cork Filler Board
 - (a) Two specimens each 115mm x 115mm ± 2,5mm shall be immersed in hydrochloric acid of a specific gravity of 1,18 at room temperature which is then brought to the boil and maintained thus for one hour when the specimens shall be removed and rinsed in water.
 - (b) The material shall be deemed to have passed the test when, after examination, the specimens show no evidence of serious disintegration, friability or lack of resilience. Discolouration or minor swelling shall not be considered as failure.

1016 Preparation and Sealing of Joint Grooves

General

- 1 All transverse joints in surface slabs, except for construction joints in CRCP shall be sealed using one of the joint seals described in Clause 1017. Additionally longitudinal joints which are sawn or widened shall be sealed.

Preparation of Joint Grooves for Sealing

- 2 Joint grooves shall be prepared in accordance with BS 5212: Part 2 and sub-Clauses 3 to 8 of this Clause.
- 3 That part of the groove former used to form the sealing groove or any temporary seal shall be removed cleanly without damaging the joint arrises to a minimum depth of 25mm where compression seals are used or otherwise to such depth as will provide an applied seal to the dimensions shown in Table 10/6, after allowing for any necessary caulking material described in sub-Clause 6 of this Clause. If joint grooves are not initially constructed to provide the minimum dimensions for the joint seals as given in Table 10/6, they shall be widened by sawing. Joint grooves formed by tapered formers need not be widened. The sealing grooves shall be cleaned out immediately after sawing using high pressure water jets, to remove all slurry from the joint, before the slurry hardens.
- 4 If rough arrises develop when grooves are made they shall be ground to provide a chamfer approximately 5mm wide. If the groove is at an angle up to 10° from the perpendicular to the surface, the overhanging edge of the sealing groove shall be sawn or ground perpendicular. If spalling occurs or the angle of the former is greater than 10° the joint sealing groove shall be sawn wider and perpendicular to the surface to encompass the defects up to a maximum width, including any chamfer, of 40mm for transverse joints and 25mm for longitudinal joints. If the spalling cannot be so eliminated then the arris shall be repaired by suitable thin bonded arris repair using cementitious materials as specified in Clause 1032.
- 5 For applied sealants the sides of the joint sealing groove shall be scoured by dry abrasive blasting. This shall not be carried out before the characteristic compressive strength of the concrete is expected to reach 15N/mm². When compression seals are used, the sides of the groove may be ground or wire brushed.

- 6 For hot and cold applied sealants, compressible caulking material, debonding strip or tape or cord compatible with the sealant, of a suitable size to fill the width of the sealing groove, shall be firmly packed or stuck in the bottom of the sealing groove to such a depth so as to provide the correct depth of seal as described in Table 10/6 with the top of the seal at the correct depth below the surface of the concrete.
- 7 All grooves shall be cleaned of any dirt or loose material by air blasting with filtered, oil-free compressed air. The groove shall be clean and dry at the time of priming and sealing.
- 8 For applied sealants the joint grooves shall be primed with the relevant primer for the hot or cold applied sealant in accordance with the manufacturer's recommendations and with BS 5212: Part 2, except that when necessary the joint grooves may be primed and sealed earlier than 14 days after construction, as soon as the grooves have been grit-blasted and cleaned.

Sealing with Applied Sealants

- 9 Sealing shall be carried out continuously along the full length of joint in any one rip, except for remedial areas. When hot or cold applied sealants are used the sealant shall be applied within the minimum and maximum drying times of the primer recommended by the manufacturer. Priming and sealing with applied sealants shall not be carried out when the naturally occurring temperature in the joint groove to be sealed is below 10°C except between 8°C and 10°C it may be carried out when the temperature is rising.
- 10 Hot-applied sealants shall be prepared and applied in accordance with the manufacturer's instructions.
- 11 The components of cold-applied sealants shall be thoroughly mixed in the correct proportions in accordance with the manufacturer's instructions. As soon as possible after mixing and within the worklife of the sealant, the material shall be dispensed into the joint, or applied using a caulking gun, to the correct level below the concrete surface. The tack-free time shall be achieved within 3 hours for machine dispensed material, or within 12 hours for hand applied material.

Testing of Applied Sealants

- 12 Test certificates shall be supplied from an appropriate organisation accredited in accordance with Clause 105 for testing sealants stating that the sealant conforms to the relevant standard in Clause 1017. Site testing of cold-applied sealants shall be in accordance with BS 5212-2. Site testing of hot applied sealants shall be in accordance with clause 6 and Appendix A of BS 2499-2 and the reference to BS 2499-1 in clause 6 of BS 2499-2 shall be replaced by IS EN 14188-1. Samples of hot applied sealants shall be taken and tested for initial penetration and resilience in accordance with IS EN 13880-2 and IS EN 13880-3 respectively and shall conform to the requirements of IS EN 14188-1.

Sealing with Compression Seals

- 13 When compression seals are used, the widths of the seal shall be selected in relation to the width of the sealing groove, the bay lengths and manufacturer's recommendations so that the estimated maximum width of the joint opening shall be not more than 70% of the original width of the seal, the estimated maximum width being calculated on the basis of a movement of 4mm per 10m run of slab. The maximum calculated width of sealing groove shall be 30mm. The depth of groove shall be such that the contact face of the seal with the side of the groove shall be not less than 20mm and that the top of the seal shall be a minimum of 3mm below the surface of the concrete.

- 14** Compression seals shall be inserted into the grooves without prior extension or rotation and, where recommended by the manufacturer, with a lubricant adhesive which is compatible with the seal and the concrete. The adhesive shall be applied to both sides of the sealing groove or the seal, or to both. The seal shall be positioned with its axis perpendicular to the concrete surface. Excess adhesive on top of the seal shall be removed to prevent adhesion of the top faces of the seal under compression. Except when compression seals are used in longitudinal joints the transverse joint seal shall be continuous across the slab and the longitudinal joint groove forming strips shall be cut to the required depth after the concrete has hardened for the transverse seal to be inserted. If compression seals are used in longitudinal joints where the grooves have been sawn after construction of the slab they shall be continuous across transverse joints, with the transverse seals butted and fixed to the longitudinal seals with adhesive.

TABLE 10/6: Dimensions of Applied Joint Seals

Type and Spacing of Joints (m)	Minimum Width mm	Minimum Depth of Seal (Note 1)		Impregnated Foam Compression Strips mm	Depth of Seal Below the Concrete Surface mm
		Cold Applied mm	Hot Applied mm		
Contraction					
15 and under	13 (Note 2)	13	15	30	5 ± 2
Over 15 to 20	20	15	30	30	5 ± 2
Over 20 to 25	30	20	25	40	5 ± 2
Expansion					
Transverse Warping	30	20	25	40	7 ± 2
Longitudinal Joints (if sealed)	10	10	13	30	5 ± 2
Gully and Manhole Slabs	10	10	13	30	0 to 5
	20	158	20	30	0 to 3

NOTE (1): The depth of seal is that part in contact with the vertical face of the joint groove. The depth of seal below the surface shall be taken at the centre of an applied seal relative to a short straight edge, 150mm long, placed centrally across the joint within 7 days of sealing.

NOTE (2): For cork seals other than in construction joints, grooves shall be 20mm width, 50mm depth.

1017 Joint Seals

- 1 Joint seals shall consist of hot or cold applied sealants or compression seals or self expanding cork seals complying with this Clause. The colour of the joint seal material shall comply with the requirements of Appendix 7/2.

Hot-applied Sealants

- 2 Hot-applied sealants shall be Type N1 or Type F, as stated in Appendix 7/1, and conforming to IS EN 14188-1.
- 3 For joints between concrete surface slabs and bituminous surfacing, hot applied Type N1 sealants conforming to IS EN 14188-1 shall be used. Alternatively polymer modified bitumen sealing strips may be used and shall be applied in accordance with the manufacturer's instructions. Hot-applied Type N1 sealants may be used in joints in asphalt kerbs laid on concrete pavements.

Cold-applied Sealants

- 4 Cold-applied sealants shall be Type N conforming to BS 5212-1 except that Type F shall be used for lay-bys and hardstandings.
- 5 For joints in kerbs and joints other than in pavements, seals may be any of the pavement sealants if they have the suitable characteristics for the application, or gunning grade cold applied plasticised bituminous rubber sealant or gunning grades of two part polysulphide-based sealants complying with IS EN ISO 11600 may be used. Alternatively, polyurethane-based sealing compounds may be used provided their performance is not inferior to IS EN ISO 11600 material.

Compression Seals

- 6 Compression seals shall be pre-compressed neoprene impregnated expanding foam sealing strip having a current NSAI Agrément or equivalent certificate or rubber seals made of polychloroprene elastomers complying with BS 2752 and conforming with the requirements of ASTM Standard D2628-91 (2005). Seals of butadiene-acrylonitrile or other synthetic rubbers may be used if certificates are produced to show that they conform to the performance requirements of ASTM Standard D2628-91 (2005) for oven ageing, oil and ozone resistance, low temperature stiffening and recovery. Seals made of ethylene vinyl acetate in microcellular form and other synthetic materials may be used in longitudinal joints and in structures if test certificates are produced to show adequate resistance to fuels and heat ageing when tested in accordance with BS 4443-4, Method 10 and IS EN ISO 2440 respectively. The compression set of any seal shall not be greater than 15% when the specimen is subjected to a 25% compression in accordance with IS EN ISO 1856. When immersed in standard oils for 48 hours at 25°C in accordance with ISO 3384 or IS ISO 1817, the volume change shall not be greater than 5%.
- 7 Compression seals shall be shaped so that they will remain compressed at all times in accordance with Clause 1016 and shall have a minimum of 20mm contact face with the sides of the sealing groove. If lubricant-adhesive is used, it shall be compatible with the seal and the concrete and shall be resistant to abrasion, oxidization, fuels and salt.

Self Expanding Cork Seal

- 8** Cork seals may be used in longitudinal joints, joints for manhole and gully slabs and for transverse joints in short lengths of individual slabs or for replaced slabs.
- 9** Self expanding cork seal for concrete pavements shall comply with the requirements of the Department of Housing and Construction, Commonwealth of Australia, Standard Specification RA SS 106 “Preformed Self Expanding Cork Joint Sealer” when tested in accordance with the same authority’s Method of Test MT RA 100 - Tests for Preformed Self Expanding Cork Joint Sealer. The self expanding cork seal shall be stored dry in the manufacturer’s wrapping until required for use.
- 10** Bonding seals to an existing slab shall be carried out up to 100m in advance of the paver.
- 11** Individual lengths of cork seal may be joined using scarf joints. A contact adhesive approved by the supplier of the cork seal shall be used to secure the joint.
- 12** Following the completion of the finishing by machine the top of the cork seal shall be exposed. The protective tape on the top edge of the cork seal shall be removed as soon as possible after the concrete has hardened, normally within 24 hours.

1018 Joints at Manhole and Gully Slabs

- 1** Manhole covers, gullies and their frames shall be isolated from the pavement slabs and be contained in separate small slabs, which shall be larger than the exterior of the manhole and gully shafts, including any concrete surround less than 150mm below the underside of the sub-base layer. The joint around the manhole or gully slab shall be vertical and incorporate joint filler board as in Clause 1015 but without dowel bars and tie bars.
- 2** Gully slabs in unreinforced concrete slabs shall be adjacent to or straddle a transverse joint, extending the gully slab as necessary to a maximum of 2m. Where this is impractical, an extra tied warping joint shall be provided adjacent to or within the gully slab and at least 2m from the next transverse joint. If the edge of an isolator slab is within 1m of any longitudinal joint the isolator slab shall be extended to that joint.
- 3** Manhole slabs in unreinforced concrete slabs shall be adjacent to or straddle transverse or longitudinal joints. If the manhole is within the middle third of the bay length a warping joint shall be constructed on one side of the manhole slab across the whole width of the bay to the nearest longitudinal joint.
- 4** Reinforcement as shown on the drawings in the Contract shall be placed in the main concrete slabs in the corners between the manhole and gully slabs and the transverse or longitudinal joints. Extra reinforcement as described in the Contract shall be placed in reinforced concrete slabs around the manhole or gully slabs.
- 5** Manhole and gully slabs shall have square corners, at all corners which are not adjacent to a transverse or longitudinal joint in the main slab.
- 6** Reinforcement as shown on the drawings in the Contract shall be placed in the gully or manhole slab and concrete Class C32/40 shall be placed by hand in the space between the main slab and the manhole frame. The concrete shall be fully compacted and finished in compliance with Clause 1025.

- 7 A sealing groove shall be made directly above the joint filler board and sealed in compliance with Clause 1016.

1019 Inspection of Dowel Bars

- 1 Compliance with Clause 1011 for the position and alignment of dowel bars at contraction and expansion joints shall be checked by measurement relative to the side form or guide wires.
- 2 When the slab has been constructed, the position and alignment of dowel bars and any filler board shall be measured after carefully exposing them across the whole width of the slab. When the joint is an expansion joint the top of the filler board shall first be exposed sufficiently in the plastic concrete to permit measurement of any lateral or vertical displacement of the board. During the course of normal working these measurements shall be carried out at a rate of one joint per 1500m length of slab or one per 5 days whichever occurs the sooner. For small areas the rate shall be one joint for up to each 100 joints.
- 3 If the position or alignment of the bars in a single joint in the slab is unsatisfactory then the next two joints shall be inspected. If only the one joint of the three is defective, the rate of checking shall be increased to one joint per day until compliance is being achieved. In the event of non-compliance in two or more successive joints, the Contractor shall revert to the construction of trial lengths and make any necessary alterations to the concrete mix, paving plant or methods until the dowel bar position and alignment is satisfactory.
- 4 After the dowel bars have been examined, the remainder of the concrete shall be removed 500mm on each side of the line of the joint, and reinstated to the requirements of the Specification. Alternatively if the dowels are examined in the penultimate joint of a day's work that joint shall be made a construction joint for the next day's work and the remainder of the concrete in the last slab may be discarded.

1020 Side Forms, Rails and Guide Wires

Side Forms and Rails

- 1 All side forms and rails shall be made of steel and be sufficiently robust and rigid to support the weight and pressure caused by the paving equipment. Side forms for use with wheeled paving machines shall incorporate metal rails firmly fixed at a constant height below the top of the forms.
- 2 The forms shall be secured by using not less than three pins for each 3m length having one pin fixed at each side of every joint. Forms shall be tightly joined together by a locked joint, free from play or movement in any direction. Forms shall be cleaned and oiled immediately before each use. The rails or running surface shall be kept clean in front of the wheels of any paving machines. The forms shall be straight within a tolerance of 3mm in 3m.
- 3 The forms shall be bedded on low moisture content cement mortar or concrete class C8/10 and set to the pavement surface level as shown on the drawings in the Contract within a tolerance of ± 3 mm. The bedding shall not extend under the slab. There shall be no vertical step between the ends of adjacent forms greater than 3mm. The horizontal alignment for forms shall be to the required alignment of the pavement edge as shown on the drawings in the Contract within a tolerance of ± 10 mm. The Contractor shall ensure that the forms are set to the correct profile immediately prior to concreting. The mortar or concrete bedding shall be broken out after use.
- 4 Side forms shall not be removed earlier than 6 hours after the completion of the construction of the slab. Care shall be taken to prevent damage to the concrete and any projecting tie bars during the removal of the forms. If the removal of forms results in any damage to the concrete the period of 6

hours shall be increased to that which is necessary to avoid further damage and the Contractor shall make good the damaged areas.

Guide Wires

- 5 A guide wire shall be provided along each side of the slab to be constructed by slip form paving plant. Each guide wire shall be at a constant height above and parallel to the required edges of the slab as shown on the drawings in the Contract, within a vertical tolerance of $\pm 3\text{mm}$. Additionally, one of the wires shall be at a constant horizontal distance from the required edge of the pavement as shown in the drawings in the Contract within a lateral tolerance of $\pm 10\text{mm}$.
- 6 The guide wires shall be supported from stakes not more than 8m apart by connectors capable of fine horizontal and vertical adjustment. The guide wire shall be tensioned on the stakes so that a 500 gramme weight shall produce a deflection of not more than 20mm when suspended at the mid-point between any pair of stakes. The ends of the guide wires shall be anchored to fixing points which shall be not closer to the edge of the slab than the row of stakes and in no circumstances shall a guide wire be anchored to a stake.
- 7 The stakes shall be positioned and the connectors maintained at their correct height and alignment from 1200 hours on the day before concreting takes place until 36 hours after the concrete has been finished. The guide wire shall be erected and tensioned on the connectors at any section for at least two hours before concreting that section.

1021 Not Used

1022 Not Used

1023 Transport and Delivery

- 1 The number of delivery vehicles provided shall be sufficient to ensure a constant supply of concrete to enable the paving plant to proceed continuously.

1024 Construction by Machine

- 1 The concrete slab shall be constructed in a continuous process by either slip-form or by fixed form paving plant in accordance with this Clause or by small paving machines or hand guided methods as in Clause 1025.
- 2 The slab may be constructed in either one or two layers. In two layer construction, the thickness of the top layer shall be not less than 50mm or twice the maximum size of the coarse aggregate, whichever is the greater, and shall be at least 15mm thicker than the depth of the groove former, if used.

Construction by Fixed Form Paving Machines

- 3 A fixed form paving train shall consist of separate, powered machines which spread, compact and finish the concrete in a continuous operation.
- 4 Concrete shall be discharged without segregation into a hopper spreader which is equipped with the means of controlling its rate of deposition on to the sub-base or on to the lower layer. The concrete shall be spread in each layer without segregation and to a uniform uncompacted density over the whole area of the slab. The deposited concrete shall be struck off to the necessary level by the underside of the hopper as it is traversed across the spreading machine. The machine shall be capable of being rapidly adjusted for changes in average and differential surcharge necessitated by

changes in slab thickness or crossfall. When the slab is constructed in two layers, the spreading of the concrete in the top layer shall follow the completion of the bottom layer within the times given in Table 10/7.

- 5 Prior to being compacted, the surface level of each loose spread layer shall be adjusted to the correct surcharge by means of rotating strike-off blades or a screw device.
- 6 The concrete shall be compacted by vibration or by a combination of vibration and mechanical tamping so as to comply with Clause 1003 throughout the full depth of the slab. Poker vibrators shall be used in each layer adjacent to the side forms and the edge of a previously constructed slab.
- 7 The initial regulation and finish to the surface of the slab shall be effected by means of a beam oscillating transversely or obliquely to the longitudinal axis of the pavement. This beam shall be readily adjustable for both height and tilt.
- 8 Joint grooves shall be constructed in compliance with Clause 1013. When grooves are wet-formed, the concrete shall be re-compacted around the former by a hand held vibrating plate compactor drawn along or on each side of the joint, prior to the final regulation of the surface by a longitudinal oscillating float.
- 9 The regulation and finishing of the surface of the slab shall be carried out by a machine which incorporates twin oblique oscillating finishing beams which shall be readily adjustable for both height and tilt. The beams shall weigh not less than 170kg/m, be of rectangular section and span the full width of the slab. The leading beam shall be vibrated. The beams shall be supported on a carriage, the level of which shall be controlled by the average level of not less than four points evenly spaced over at least 3,5m of the supporting rail, beam, or slab, on each side of the slab that is being constructed. Except for CRCB slabs, the final regulation of the surface of the slab shall be provided by a longitudinal oscillating float, travelling across the slab. After the final regulation and before the macrotexture is applied, any excess concrete on top of the joint groove former, where present, shall be removed. Additionally the longitudinal oscillating float shall complete the traverse of the slab in both directions within the length of the float and shall have a total longitudinal stroke of 200mm to 300mm.
- 10 The longitudinal oscillating float shall have a minimum length of 3m and a minimum constant width of 250mm with a maximum weight of 10kg/m. The edges of the float shall be curved or chamfered.
- 11 A minimum length of 500mm of longitudinal oscillating float shall be within the length of the machine tracks or wheels.
- 12 When a concrete slab is constructed in more than one width, flanged wheels on the paving machines shall not be run directly on the surface of any completed part of the slab. The second or subsequent slabs shall be constructed either by supporting machines with flanged wheels on flat-bottom section rails weighing not less than 15kg/m laid on the surface of the completed slab, or by replacing the flanged wheels on that side of the machines by smooth flangeless wheels. Before flangeless wheels or rails are used, the surface regularity of the slab over which they are to pass shall comply with Clause 702 and its surface shall be thoroughly cleaned and brushed to remove all extraneous matter. Flangeless wheels or rails shall be positioned sufficiently far from the edge of the slab to avoid damage to that edge.

Construction by Slip-form Paving Machine

- 13 A slip-form paving train shall consist of powered machines which spread, compact and finish the concrete in a continuous operation.

- 14** The slip-form paving machine shall compact the concrete by internal vibration and shape it between sliding side forms or over fixed side forms by means of either a conforming plate or by vibrating and oscillating finishing beams.
- 15** The concrete shall be deposited without segregation in front of the slip-form paver across its whole width and to a height which at all times is in excess of the required surcharge. The deposited concrete shall be struck off to the necessary average and differential surcharge by means of a strike-off plate or a screw auger device extending across the whole width of the slab. The equipment for striking off the concrete shall be capable of being rapidly adjusted for changes of the average and differential surcharge necessitated by changes in slab thickness or crossfall.
- 16** The level of the conforming plate and finishing beams shall be controlled automatically from the guide wires by sensors attached at the four corners of the slip form paving machine. The alignment of the paver shall be controlled automatically from the guide wire by at least one sensor attached to the paver. The alignment and level of ancillary machines for finishing, texturing and curing of the concrete shall be automatically controlled relative to the guide wire or to the surface and edge of the slab.
- 17** Slipform paving machines shall have vibration of variable output, with a maximum energy output of not less than 2,5kW per metre width of slab per 300mm depth of slab for a laying speed of up to 1.5m per minute or pro rata for higher speeds. The machines shall be of sufficient mass to provide adequate reaction on the traction units to maintain forward movements during the placing of concrete in all situations.
- 18** Except for CRCB slabs, the final regulation of the surface slab shall be provided by a longitudinal oscillating float travelling across the slab. The longitudinal float shall comply with the requirements of sub-Clauses 9, 10 and 11 of this Clause. Additionally, the longitudinal float shall either be a separate machine closely following a slipform paver or alternatively it shall be attached to a slipform paver in such a manner that it functions effectively and does not adversely affect the performance of the paver or the surface of the slab.
- 19** Joint grooves shall be constructed in compliance with Clause 1013. Where grooves are wetformed the concrete shall be compacted around the former by a separate vibrating plate compactor with twin plates. The groove former shall be compacted to the correct level by a vibrating pan which may be included with the transverse joint finishing beam. Final finishing shall be carried out in accordance with sub- Clause 18 of this Clause. Any excess concrete on top of the groove former shall be removed before the surface is macrotextured.
- 20** Where a concrete slab is constructed in more than one width or where the edge needs to be matched for one level to another section of surface slab, and the surface levels at the edges are not achieved, the slab shall be supported by separate side forms placed before or after the paver to ensure that edge levels meet the required tolerances.

General

- 21 While the concrete is still plastic its surface shall be brushed to comply with the macrotexture requirements specified in Clause 1026. The surface and edges of surface slabs and CRC bases shall be cured in compliance with Clause 1027.
- 22 The spreading, compacting and finishing of the concrete shall be carried out as rapidly as possible and the paving operation shall be so arranged as to ensure that the time between the mixing of the first batch of concrete in any transverse section of the slab and the application of the sprayed curing membrane to the surface of that section shall not exceed those given in Table 10/7.
- 23 Each bay in jointed concrete surface slabs shall be consecutively numbered near the verge, next to a transverse joint while the concrete is plastic. In continuously reinforced concrete pavement the slab shall be marked with the chainage at intervals not greater than 50m apart.

1025 Construction by Small Paving Machines or Hand Guided Methods

- 1 As an alternative to fixed form or slip-form paving trains, the concrete slab may be constructed using parts of trains, small paving machines, truss type finishing beams or hand guided methods. Hand tamping beams may only be used for short lengths or infill bays or tapers. Reinforcement, dowel bars and tie bars shall be supported in position in accordance with Clauses 1008, 1011 and 1012 respectively, except where two layer construction is used and reinforcement is placed on the bottom layer.

TABLE 10/7: Maximum Working Times

Temperature of concrete at discharge from the delivery vehicle	Reinforced concrete slabs constructed in two layers, without retarding admixtures		All other concrete slabs	
	Mixing first layer to finishing concrete	Between layers	Mixing first layer to finishing concrete	Between layers
Not more than 25°C	3 hours	Half hour	3 hours	1.5 hours
Exceeding 25°C but not exceeding 30°C	2 hours	Half hour	2 hours	1 hour
Exceeding 30°C	Unacceptable for paving	-	Unacceptable for paving	-

- 2 The concrete shall be spread uniformly without segregation or varying degrees of pre-compaction, by conveyor, chute, blade or auger. The concrete shall be struck off by a screed or auger so that the average and differential surcharge is sufficient for the surface of the slab to be at the correct levels after compaction of the concrete.
- 3 The concrete shall be compacted by vibrating finishing beams across the slab and with vibrating pokers adjacent to the side forms or the edge of a previously constructed slab. In addition, internal poker vibration shall be used for slabs thicker than 200mm and may be used for lesser thicknesses. When used, the pokers shall be at points not more than 500mm apart over the whole area of the slab, or drawn continuously across the slab in front of the finishing beams.
- 4 The finishing beams shall be metal with a contact face at least 50mm wide. They shall be rigid or supported by a frame or truss without sag across the width of slab being paved. The beams shall be supported on rails or forms or an adjacent slab and shall be moved forward at a steady speed of

0,5m to 2m per minute whilst vibrating, to compact the concrete and to produce a smooth surface finished to the correct crossfalls, crowns and levels relative to the top of the forms or adjacent slab.

- 5 Joint grooves shall be constructed in compliance with Clause 1013. Any irregularities at wet-formed joint grooves shall be rectified by means of a vibrating float at least 1,0m wide drawn along the line of the joint. The whole area of the slab shall be regulated by two passes of a scraping straight edge not less than 1,8m wide or by a further application of a twin vibrating finishing beam. Any excess concrete on top of the groove former shall be removed before the surface is macrotextured.
- 6 The surface shall be brush-textured as described in Clause 1026.
- 7 The surface shall be cured in compliance with Clause 1027, within the time to completion given in Table 10/7.

1026 Finished Surface Requirements

Macrotexture of Running Surfaces

- 1 The finished surface of the pavement shall comply with the requirements of Clause 702. Where a pavement area does not comply with the Specification in any respect the full extent of the surface which does not comply shall be rectified in accordance with Clause 702.
- 2 After the final regulation of the surface of the slab and before the application of the curing membrane, the surface of concrete slabs to be used as running surfaces shall be brush macrotextured in a direction at right angles to the longitudinal axis of the carriageway. The macrotexture shall be applied evenly across the slab in one direction by a brush not less than 450mm wide. The macrotexture shall be uniform both along and across the slab.
- 3 The macrotexture depth shall be determined by the volumetric patch technique as described in IS EN 13036-1. Tests shall be taken within 100m of commencement of paving and thereafter at least once for each day's paving at the times after construction as given below and in the following manner: 10 individual measurements of the macrotexture depth shall be taken at least 2m apart anywhere along a diagonal line across a lane width between points 50m apart along the pavement. No measurement shall be taken within 300mm of the longitudinal edges of a concrete slab constructed in one pass.
- 4 Macrotexture depths shall be as required in Table 10/8.
- 5 Where the required macrotexture depth is found to be deficient the Contractor shall make good the texture across the full lane width over lengths necessary to comply with the requirements of Table 10/9, by retexturing the hardened concrete surface as described in Clause 1029. Failure to achieve a satisfactory minimum macrotexture depth by random grooving shall result in the removal of the full thickness of the slab to the extent required to permit reconstruction of the slab in accordance with the Specification. If the macrotexture depth is excessive the surface shall be planed or ground or otherwise treated over lengths necessary to comply with the requirements of Table 10/8. The treatment shall not affect the requirements of Clause 702 in respect of surface levels or surface regularity.

TABLE 10/8: Macrotexture Depths

Time of Test	Required Macrotexture Depth (mm)		
		Specified Value	Tolerance
(i) Between 24 hours and 7 days after the construction of the slab or until the slab is first used by vehicles	An average of 10 measurements	1,00	± 0,25
(ii) Not later than 6 weeks before the road is opened to public traffic	An average of 10 measurements	1,00	+ 0,25 - 0,35

Texture of Concrete Bases

- 6 The surface of wet-laid concrete bases shall be roughened before the application of any curing compound by brushing with a wire brush or stiff broom.

1027 Curing

- 1 Immediately after the surface treatment described in Clause 1026, the surface and exposed edges of surface slabs shall be cured for a minimum period of 7 days, by the application of an approved resin based aluminised curing compound, or polythene sheeting or an approved sprayed plastic film which hardens into a peelable plastic sheet and which shall be removed before road marking and opening to traffic. Where the concrete is to receive a thin surfacing overlay, the surface and exposed edges shall be cured for a minimum of 7 days by the application of a curing agent which is compatible with the bond coat specified for the thin surfacing.
- 2 Resin based aluminised curing compound shall contain sufficient flake aluminium in finely divided dispersion to produce a complete coverage of the sprayed surface with a metallic finish. The compound shall become stable and impervious to evaporation of water from the concrete surface within 60 minutes of application and shall have an efficiency index of 90% when tested as described in BS 7542.
- 3 The curing compound shall not react chemically with the concrete to be cured and shall not crack, peel or disintegrate within three weeks after application.
- 4 Prior to application, the contents of any containers shall be thoroughly agitated. The curing compound shall be mechanically applied using a fine spray on to the surface at a rate of at least 0,22l/m². For the sides of slip-formed slabs or when the side forms are removed within 24 hours and for small areas where mechanical application cannot be used, the compound shall be sprayed by hand lance at a rate of at least 0,27l/m². The rate of spread shall be checked during construction of each trial length and for each 1000m² of treated slab.
- 5 The mechanical sprayer shall incorporate an efficient mechanical device for continuous agitation and mixing of the compound in its container during spraying.

- 6 Continuously reinforced concrete bases shall be cured in accordance with this Clause. Immediately prior to laying the bituminous surfacing or upper base, a cationic bituminous tack coat shall be applied in accordance with Clause 920 at a rate between 0,35l/m² to 0,55l/m².
- 7 To achieve high early strength for early use by vehicles, insulation blankets as described in Clause 1045 shall be used for accelerated curing.

1028 Trial Length

General

- 1 Unless otherwise described in Appendix 7/1, the Contractor shall demonstrate the constituent materials, concrete proportions, plant, equipment and methods of construction that are proposed for concrete paving, by first constructing a trial length of slab, at least 150m but not more than 300m long for mechanised construction, and at least 30m long for hand guided methods. The concrete proportions decided by trial concrete mixes may be adjusted during the trial but shall not be changed once the trial length has been satisfactorily completed unless the Contractor lays a further trial area to assess the suitability of the proposed changes.
- 2 Except in rapid construction projects and unless otherwise described in Appendix 7/1, at least three months prior to the construction of the trial length of surface slabs or CRCB the Contractor shall submit a detailed description of the proposed constituent materials, concrete proportions, plant, equipment and construction methods. No trials of new constituent materials, plant, equipment or construction methods; nor any development of them shall be permitted either during the construction of the trial length or in any subsequent paving work, unless they form part of further satisfactory trials.
- 3 The trial length shall be constructed in two parts over a period comprising at least part of two separate working days, with a minimum of 75m constructed each day when mechanised paving plant is used and a minimum of 15m on each day for hand guided methods. The trial length shall be constructed at a similar rate to that which is proposed for the main construction in the Works.
- 4 At least two transverse joints and one longitudinal joint of each type that are proposed for unreinforced concrete slabs and jointed reinforced concrete slabs in the main construction in the Works shall be constructed and assessed in the trial length. If in the trial length expansion joints are not demonstrated, the first 2 expansion joints and at least the first 150m of longitudinal construction joint for mechanised paving, or 30m for hand guided method of construction laid in the main construction in the Works, shall be considered the trial length for these joints. One construction joint shall be demonstrated in each trial length of CRCP or CRCB.

Assessment

- 5 The trial length shall comply for strength and density with the Specification in all respects, with the following additions and exceptions:

Surface Levels and Irregularity

- (i) In checking for compliance with Table 7/1 the levels shall be taken at intervals of not more than 2,5m along any line or lines parallel to the longitudinal centre line of the trial length.
- (ii) The maximum number of permitted irregularities of pavement surfaces shall comply with the requirements of Table 7/2 for 300m lengths. Shorter trial lengths shall be assessed pro-rata based on values for a 300m length.

Joints

- (iii) At least 3 cores of minimum diameter 100mm shall be taken from the slab at joints to check the lateral and vertical location of joint grooves and bottom crack inducers.
- (iv) Alignment of dowel bars shall be inspected as described in Clause 1019 in any two consecutive transverse joints. If the position or alignment of the dowel bars at one of these joints does not comply with Clause 1011 but if that joint remains the only one that does not comply after the next 3 consecutive joints of the same type have been inspected then the method of placing dowels shall be deemed to be satisfactory. In order to check sufficient joints for dowel bar alignment without extending the trial length unduly, the Contractor may construct joints at more frequent joint intervals than the normal spacing required in Appendix 7/1.
- (v) If there are deficiencies in the first expansion joint that is constructed as a trial the next expansion joint shall be a trial joint. Should this also be deficient, further trial expansion joints shall be made as part of a trial length. Deficient expansion joints shall not form part of the Works.

Position of Reinforcement and Tie Bars

- (vi) Compliance with Clause 1008 for the position of steel reinforcement and Clause 1012 for the position and alignment of tie bars shall be checked by drilling additional cores from the slab unless they can be determined from cores taken for density assessment.

Completion of Trial

- 6 The Contractor shall not proceed with normal working unless the trial length complies with the Specification and any earlier defective trial lengths have been removed, unless they can be remedied to comply with the Specification.
- 7 After satisfactory completion of the trial length, the constituent materials, concrete proportions, plant, equipment and construction methods shall not thereafter be changed, except for normal adjustments and maintenance of plant, unless the Contractor lays a further trial length as described in this Clause to demonstrate that the changes will not adversely affect the Works or agrees the changes with the Employer's Representative.

Rejection and Further Trials

- 8 Trial lengths which do not comply with the Specification, with the exception of areas within the pavement surface which can be remedied in accordance with Clause 1029, shall be removed and the Contractor shall construct a further trial length.

1029 Texturing of Hardened Concrete

- 1 Worn, rain damaged or inadequately textured surface slabs shall be macrotextured by sawing grooves in the hardened concrete surface at right angles to the longitudinal axis of the pavement with machines using diamond or other abrasive cutting discs.
- 2 Grooves shall be irregularly spaced and shall be not less than 2mm and not more than 5mm wide. The sequence of distances between groove centres in mm shall be: 40, 45, 35, 45, 35, 50, 30, 55, 35, 30, 50, 30, 45, 50, 30, 55, 50, 40, 35, 45, 50, 40, 55, 30, 40, 55, 35, 55. A tolerance of ± 3 mm shall

be allowed on each of the spacings. The minimum width of grooving head shall be 500mm and a head not providing a complete sequence of spacings shall use the number of spacings appropriate to its width commencing at the start of the sequence.

- 3 Groove depths shall be measured using a tyre tread depth gauge and measurements shall be taken as follows:
 - (i) At 10 locations at least 2m apart along a diagonal line across a lane width between points 50m apart longitudinally. No measurement shall be taken within 300mm of the longitudinal edge of a slab.
 - (ii) At each of the 10 locations the depth of 10 adjacent grooves shall be measured.
 - (iii) Where a grooved area is less than 50m in length the locations where measurements are taken shall be as (i) but the number shall be proportional to the requirements for 50m.
 - (iv) The average of each set of 10 measurements shall be not less than 3mm, nor greater than 7mm.
- 4 Slurry from the sawing process shall be prevented from flowing into joints, drains or into lanes being used by traffic, and all resultant debris from the grooving shall be removed.

1030 Not Used

1031 Measurement of Macrotexture Depth – Volumetric patch Technique

- 1 The macrotexture depth of the road surface will be determined using the method described and the equipment specified in IS EN 13036-1.

1032 Thin Bonded Repairs

Materials

- 1 Cement mortar shall be used for depths less than 20mm and fine concrete for greater depths. Resin mortar may only be used for small patch repairs less than 1 metre long and less than 30mm in depth and where insufficient time for adequate curing of a cementitious cement mortar exists.
- 2 The cements, aggregates, admixtures and water shall comply with Clause 1001. The sand (i.e. fine aggregate) for mortars or fine concrete shall be within the limits of 0/4 (CP), 0/4 (MP), 0/2 (MP) or 0/2 (F/P) of IS EN 12620. Coarse aggregate for fine concrete shall be (4/10) single sized aggregate complying with IS EN 12620. All aggregates shall have the same thermal properties as the aggregate in the original concrete, and match other properties as closely as possible. Filler and aggregate for resin mortars shall be pre-packed in the correct proportions and mixed with the resin all in accordance with the manufacturer's instructions.
- 3 The proportions of cement, admixtures, additives to water and aggregates shall be sufficient to provide high early strength mortar or fine concrete or concrete complying with Clauses 1001, 1003 and 1004. For cement mortar the sand (i.e. fine aggregate) to cement ratio shall not be greater than 3. For resin mortar the sand content shall be in accordance with the manufacturer's requirements in the range between 7 and 11 to 1 of resin. High early strength concrete shall be able to achieve 25N/mm² in less than 48 hours. For thin bonded repairs using high early strength concrete less than 30mm depth, air entrainment is not required.

Procedure

- 4 Mark out the area to be rectified parallel and perpendicular to the axis of the road. Cut a groove around the perimeter at least 10mm deep without overcutting into the adjacent slab. Carefully cut out the concrete to the required depth, with a vertical face without undercutting the adjacent slab.
- 5 If a joint is included in the area to be rectified, fix a groove former or corkseal along the line of the joint by chasing out a groove. For joints on the perimeter fix the groove former or corkseal by adhesive to the adjacent slab.
- 6 For cementitious repairs, wet the area of the patch. Keep it wet until the repair material is ready to be placed. Remove excess water, prime the surfaces with cement grout or bonding agent, spread the repair material immediately before the primed surface is dry, with sufficient surcharge. Thoroughly compact it by vibration ensuring full compaction at the edges and corners.
- 7 Retexture the surface to match the surrounding concrete and cure in accordance with Clause 1027.
- 8 For resin mortar repairs, ensure the area is dry before application of the primer. Place the repair material within the time allowed by the manufacturer for the primer, and compact it well into the edges to the patch. Apply a brush texture to match the original.

1033 Full Depth Repairs and Reinstatements

General

- 1 Full depth repairs shall be repairs which will require full depth reinstatement of the concrete slab in accordance with this Clause to the extent required by the **Employer's Representative** [Specialist responsible for the design of the pavement], which repairs may also require reinstatement of sub-base. Full width repairs shall be repairs over the full width of a bay or bays. Part width repairs shall be repairs over part of the width of a bay or bays. A bay shall be that portion of the concrete pavement bounded by adjacent longitudinal and transverse joints.
- 2 The area of concrete to be removed shall be marked out perpendicular to and parallel to the axis of the road. For continuously reinforced concrete slabs (CRCP or CRCB) the edge of the repair shall be not less than 0,5m from the nearest crack and not less than 3m from a transverse construction joint at ground beam anchorages. Where this and the provisions of sub-Clause 3 of this Clause would otherwise require a longitudinal repair joint within 1m of the existing longitudinal joint or edge, the repair shall be extended to align with that longitudinal joint or edge.

Part Width Repairs

- 3 Providing all the following criteria are met, part width repairs may be carried out in accordance with sub-Clause 4 of this Clause:
 - (i) the transverse width of the repair shall not exceed 45% of the width of the slab under repair; and
 - (ii) the longitudinal joint which would be formed by the repair shall not occur within the wheeltrack; and
 - (iii) the minimum transverse width of the repair shall not be less than 1,0m.

If these criteria and those in sub-Clause 2 of this Clause cannot be met, a full-width repair shall be made in accordance with this Clause.

Full Width Repairs

- 4 For full width repairs the following criteria shall apply unless otherwise specified in Appendix 7/2:
- (i) Repair lengths which do not replace an existing transverse joint shall be constructed with two transverse contraction joints and the longitudinal joint shall have tie bars in repair lengths which are greater than 1 metre.
 - (ii) Repair lengths which replace a single existing transverse joint shall be constructed with two transverse joints: one expansion and one contraction. The new expansion joint shall be formed at the end which will have the shortest longitudinal distance between this joint and the joint in the adjacent lane(s). The longitudinal joint(s) between the existing joint(s) and the new expansion joint shall be constructed without tie bars and shall have 5mm thick compressible foam within the joint for the full depth of the concrete slab. The longitudinal joint between the new contraction joint and the joint in the adjacent bay(s) shall be constructed with tie bars where the exposed length so permits.
 - (iii) Repair lengths which replace more than one existing transverse joint shall be constructed with transverse joints to match expansion and contraction joints in the adjacent bay(s). Where the repair length does not replace an existing expansion joint, one end joint shall be formed as an expansion joint. Except for the end joints all transverse joints shall be formed to coincide with the existing transverse joints. Where one end joint is an expansion joint, the longitudinal joint(s) between the existing joint(s) and the new expansion joint shall be constructed without tie bars and shall have 5mm thick compressible foam within the joint for the full depth of the concrete slab. All other longitudinal joints shall be constructed with tie bars.

Repair Work

- 5 A groove of 40mm nominal depth but less than the depth of any reinforcement shall be sawn around the perimeter. For jointed slabs, the saw-cut shall be full depth to provide the face for a new joint. There shall be no over-cutting into the adjacent slab. Additional cuts within the repair area may be made to ease removal of the redundant portion of the slab. At internal corners full depth holes across the corners at the limits of the saw cuts shall be drilled prior to breaking out. The line of cut shall not vary by more than ± 25 mm throughout its length from the set out line. All sawn edges shall be perpendicular or parallel to the sides and surfaces of the slab. When sawing operations have been completed, and before any other operations are commenced, the surface of the carriageway shall be thoroughly cleaned of the slurry produced by sawing and of any other detritus.
- 6 The concrete shall be carefully broken out without undercutting the slab or damaging adjoining slabs. If reinforcement has to be removed sufficient shall be left for a lap length, except where a dowelled joint is being made. Reinforcement shall not be bent and subsequently straightened. Slurry from sawing, slab breaking, repair materials and other debris shall be prevented from entering joints and grooves in adjacent areas.
- 7 When a new joint is required holes shall be drilled of the appropriate size and depth for dowels or tie bars according to the type of joint. These holes shall be thoroughly cleaned of debris and dust. This shall include but not be limited to the use of oil-free compressed air at a pressure of not less than 0,5N/mm². Dowels and tie bars shall comply with the requirements of Clauses 1011 and 1012 respectively. Epoxy mortar shall be to the manufacturer's recommendation for this specific application. The holes shall be filled with epoxy mortar, the mortar being injected to the rear of the hole to avoid air entrapment. The dowel bars shall be inserted into the holes before the initial set of the mortar. If cartridges of epoxy mortar are used they shall be inserted into each hole, the dowel bar inserted

through the cartridges and rotated for 1 minute to ensure that the epoxy mortar is well mixed. After insertion the dowels and tie bars shall be within the specified tolerances for alignment.

Where repairs straddle a movement joint with an adjacent slab, tie bars shall be omitted and the joint between the slabs debonded to ensure that movement patterns are not restricted.

Where Appendix 7/2 or the drawings so require, full bay replacement shall be made and this may require an expansion joint or a contraction joint to be provided at the ends of the replaced bay.

- 8** Expansion joint filler shall be fixed to one of the transverse joints. In the other transverse joint, contraction joint groove forming strips or cork seal shall be fixed to the edges of the adjacent concrete.
If the repair is adjacent to another slab, bond between the two slabs shall be prevented by providing full depth 5mm thick compressible foam strips to Clause 1014 along the longitudinal joint between them.
- 9** The sub-base layer and any separation membrane shall be reinstated as necessary to comply with Series 800 and Clause 1007 respectively.
Defective sub-base material shall be removed and the sub-base reinstated to the correct level with the material described in Appendix 7/2. Reinstatement of the sub-base shall be completed before new dowel and tie bars are fixed at the joints.
- 10** New reinforcement shall be lapped and welded or tied. The length of tied laps shall be 35 bar diameters or 450mm whichever is the greater for longitudinal bars and 300mm for transverse bars. Welded laps shall be 150mm minimum length unless a butt-weld process has been used in accordance with Clause 1717.
- 11** The reinstated concrete shall be placed, spread, compacted and finished as specified in Clause 1025. Particular care shall be taken to ensure full compaction at the edges. The concrete shall be normal or high early strength pavement concrete, complying with Clauses 1001 to 1005 and shall achieve the required characteristic strength prior to opening to traffic.

Crack Repairs

- 12** Stitched crack repairs shall be either
Type 1 - Staple Tie Bar Repair
Type 2 - Diagonal Tie Bar Repair
as described in Appendix 7/2 and compliant with sub-Clauses 13 and 14 of this Clause. The extent of crack repairs shall be determined by inspection after the surface has been cleaned.
- 13** For Type 1 crack repairs, slots 25 - 30mm wide by 470mm long at 600mm centres and at right angles to the line of the crack shall be chased out to a depth such that, when bedded, the tie bars lie between $\frac{1}{3}$ and $\frac{1}{2}$ of the depth of the slab below the surface. Holes of 25mm - 30mm diameter by 50mm deep shall be drilled at each end of the slot and the slots cleaned out using oil free compressed air.

When in a dry state the slots shall be primed and the staple tie bars placed into beds of epoxy mortar and covered to a minimum depth of 30mm with the same material. The sides of the slots shall be cleaned of loose material and the slots filled with thoroughly compacted epoxy or cementitious mortar as described in Appendix 7/2.

After curing a groove shall be sawn along the line of the crack and sealed in accordance with Clause 1016.

- 14** For Type 2 crack repairs drilling points shall be marked out at a distance from the crack equivalent to the depth of the slab, at 600mm intervals along the crack with alternate points on opposite sides of the crack.

Holes of 16 mm minimum diameter shall be drilled at right angles to the crack and at approximately 26° to the surface of the slab to a depth which allows 50mm cover at the bottom of the slab. These holes shall be thoroughly cleaned of debris and dust.

12mm diameter Grade 460 deformed steel tie bars shall be notched at a point which will ultimately be 50mm below the slab surface when the bars are fully inserted into the hole.

Each hole shall be filled with epoxy mortar and its quantity adjusted to ensure that when the tie bar is fully inserted the level of the mortar is up to a point which is 25mm below the notch on the tie bar. Such adjustment of the epoxy mortar and the final insertion of the tie bar shall be done rapidly to ensure its completion before the initial set of the mortar. After the epoxy mortar has set, the length of tie bar above the notch shall be broken off. Once all these bars have been broken off, the tops of all these holes shall be filled with epoxy mortar.

If cartridges of epoxy mortar are used the bars shall be inserted through the cartridges and rotated for 1 minute to ensure that the adhesive is well mixed.

Joint Grooves and Seals

- 15** Longitudinal joint grooves shall be re-cut where directed in Appendix 7/2 using the following procedure. The longitudinal joint shall be saw cut to a nominal width of 10mm to encompass the existing joint and to sufficient depth to remove the existing sealant approximately 25mm deep. Where existing sealant or traces thereof cannot be removed within the 10mm saw cuts the groove shall be widened to enable all existing sealant to be removed.

The groove sides shall be vertical, and the horizontal alignment of the groove shall be straight and parallel to the edge of the slab. The concrete and sealant shall be removed between the saw cuts without damaging the sides of the groove.

The base of the groove shall be formed to a uniform profile suitable for the application of debonding tape or caulking material.

Any residual traces of sealant or detritus shall be removed from the groove and the groove prepared for sealing in accordance with Clause 1017.

- 16** Transverse joint grooves shall be recut where directed in Appendix 7/2 using the following procedure.

The transverse joint shall be saw cut to form a groove to satisfy the dimension of applied joint seals as specified in Table 10/6 allowing for debonding tape or any necessary caulking material of at least 5mm uncompacted depth and to encompass the existing joint.

The groove sides shall be vertical, and the horizontal alignment of the groove shall be straight and parallel to the line of the joint.

The concrete and sealant shall be removed between the saw cuts without damaging the sides of the groove.

The base of the groove shall be formed in accordance with Clause 1017.

Any residual traces of sealant or detritus shall be removed from the groove and the groove prepared for sealing in accordance with Clause 1016.

- 17 Unless cork sealants complying with Clause 1017 have been used, the joints shall be sealed in accordance with Clause 1016.

1034 Summary of Rates for Sampling and Testing Concrete for Pavement Layers

- 1 Unless otherwise stated in Appendix 1/5, Table 10/9 summarises the minimum rates of sampling and testing of specimens to the Specification.
- 2 Samples for testing shall be taken at the point of placing or from the relevant pavement layer.

1035 to 1042 Not Used

1043 Foamed Concrete

- 1 Foamed concrete used in reinstatements shall comply with the requirements of the “Specification for the Reinstatement of Openings in National Roads” issued by the National Roads Authority.
- 2 Foamed concrete used for backfilling excavations, including trench reinstatement, under road pavements shall have the following compressive strengths:
 - (i) A minimum cube compressive strength of 4N/mm² at an age of 7 days.
 - (ii) A maximum cube compressive strength of 10N/mm² at an age of 7 days.

TABLE 10/9: Rates for Sampling and Testing Concrete for Pavement Layers

Clause	Test	Rate (the greater number shall be used)	
1002	Air Content	a) Main slab	1 per 300m ² or 6 per day
		b) slabs less than 300m ²	1 per 20m length or 3 per day
1003	Density	a) Main slab and trial length	A minimum of 3 cores at a rate of 1 core per 1000m ²
1004	Strength	a) Main Slab	3 cores for areas up to 3000m ² and 1 additional core per further 1000m ²
		b) Trial length	At least 6 cores, half to be tested 7 days and half at 28 days
1005	Consistence	a) Main slab – initial 50m ³ Subsequently	3 samples 1 per 150m ³ or 1 per production day
		b) Slabs less than 150m ³	3 samples in first 50m ³ then 1 more
1016	Hot or cold applied joint sealants	Penetration Test	One sample per 1000m joint or at least one per day
1019	Inspection of dowel alignment	a) Main slab	1 joint per 1500m length or 1 joint per 5 days whichever is the sooner
		b) Slabs less than 1500m in length	At a rate of one joint for up to each 100 joints
		c) Trial lengths	2 consecutive joints. If one defective, inspect next 3 consecutive joints.
1026	Macrotexture depth	Each lane width	One within 100m of commencement of paving and thereafter at least one set of 10 measurements per day's work.

The compressive strength shall be determined by testing foamed concrete cubes which have been made in accordance with IS EN 12390-1 except that the foamed concrete shall be placed in the mould without any tamping or vibration other than gently rocking the mould on a firm base. The test cubes shall be cured in accordance with IS EN 12390-2 and tested for compressive strength in accordance with IS EN 12390-3.

- 3 All aggregate used in foamed concrete shall pass a 6,3mm sieve and shall comply with the MP and FP grading limits given in IS EN 12620. Larger size aggregate may be used provided it can be shown to be practicable.
- 4 After placing, foamed concrete shall not be tamped, or otherwise compacted.
- 5 Reinstatement of the sub-base and base over the foamed concrete shall not be carried out until the foamed concrete has attained sufficient strength to allow compaction of the sub-base and base material.

1044 Pavements with an Exposed Aggregate Concrete Surface

General

- 1 Pavements with an exposed aggregate concrete surface shall comply with all the requirements of this Series except where otherwise specified in this Clause.
- 2 Clauses 1026, 1029 and 1031 shall not apply.
- 3 The concrete slab shall be laid in either a single layer or in two layers. If laid in two layers the surface layer shall be laid monolithically with the lower layer.
- 4 The Contractor shall carry out trials, as specified in sub-Clauses 31 to 39 of this Clause, to demonstrate that the materials, concrete proportions and methods for exposing the aggregate will meet the requirements of this Clause.

Quality of Concrete in the Slab

- 5 The surface layer concrete shall comply with the following requirements:-
 - (i) The surface layer shall be not less than 40mm thick. The coarse aggregate shall comply with the size requirements of Appendix 7/1.
 - (ii) For 6,3/10 mm coarse aggregate or 4/8mm coarse aggregate as required in Appendix 7/1, the amount of aggregate retained on the 10mm sieve and 8mm sieve respectively shall not exceed 3% by mass. The aggregate passing the 6,3mm sieve and 4mm sieve respectively shall not exceed 10% by mass.
 - (iii) The fine aggregate grading shall comply with the 0/2 (FP) or 0/1 (FP) grading in IS EN 12620 except that not less than 99% of the mass of the material shall pass the 2mm sieve.
 - (iv) The coarse aggregate shall comprise at least 60% by mass of the oven dry constituents of the concrete.
 - (v) The polished stone value (PSV) and the aggregate abrasion value (AAV) of the coarse aggregate determined in accordance with IS EN 1097-8 shall be as specified in Appendix 7/1. The Category of flakiness index of the aggregate is FI₁₅.
 - (vi) Hardness and durability of the coarse aggregate shall be as described in sub-Clauses 901.5 and 901.6.
 - (vii) The type of cement used in the concrete shall be limited to Class 42,5N/42,5R Portland cement CEM I complying with IS EN 197-1. The minimum cement content of the concrete shall be 375kg/m³ and the maximum free water/ cement ratio shall be 0,40.
 - (viii) The air content, density and strength requirements shall be as required in Clauses 1002, 1003 and 1004 respectively.

General Construction Requirements

- 6 The concrete paving equipment shall be in accordance with the requirements of this Series. The general construction requirements shall be in accordance with the requirements of this Series except where otherwise stated in this Clause:
 - (i) The concrete carriageway paving operation shall be undertaken as not less than a single lane width of construction using either slipform paving machines or fixed form paving machines.

- (ii) The concrete surface layer shall be fed, spread, compacted, regulated and finished using equipment with elements to obtain the required uniform distribution and bonded embedment of the selected aggregate in the finished road surface.
- (iii) The spread concrete shall be compacted in such a manner that base layer concrete is not drawn into the surfacing and selected aggregate is uniformly present in the finished road surface.
- (iv) The surface layer shall be compacted and shaped to line and level by a combination of either internal vibration and fixed conforming plate or vibrating conforming plate.
- (v) The final regulation of the surface layer shall be provided by a transverse finishing screed in advance of a longitudinal oscillating float in accordance with Clause 1024, travelling across the slab before the application of a retarder complying with IS EN 934-2.

Finished Surface Requirements

- 7 The finished surface of the pavement shall comply with the requirements of Clause 702. Where a pavement area does not comply with the Specification for regularity, surface tolerance, thickness, material properties or compaction or contains surface depressions, the full extent of the surface which does not comply with the Specification shall be rectified by cutting out the full depth of the slab. It shall be replaced with a new slab complying with the procedures set out in Clause 1033 to the extent required to obtain compliance with the Specification.

Production of an Exposed Aggregate Surface

- 8 In order to obtain a suitable exposed aggregate surface the main requirement shall be the removal of the surface mortar from the top of the slab to produce an exposed aggregate finish. This objective may be achieved by the application of a suitable cement set retarder which is sprayed on the surface of the fresh concrete immediately after it has been levelled and finished. Retarded mortar shall be removed by wet or dry brushing generally no sooner than when the surface concrete has reached a maturity of 16 hours at 20°C or after a suitable interval determined by trial, to achieve the requirements of sub-Clause 27 of this Clause.

Retarder

- 9 The composition and viscosity of the retarder shall be such that it can be spread at an adequate and uniform rate over the surface of the concrete slab in order to ensure adequate aggregate exposure during the subsequent brushing operation.
- 10 The retarder shall contain a pigment in sufficient quantity to give an even uniform colour after it has been sprayed on to the slab surface. The pigment shall be fully degraded by exposure to ultra-violet light without leaving any residue that is detrimental to the surface of the concrete.
- 11 The chemical composition of the retarder and of the curing compound shall be such that they do not react adversely following the application of the curing compound to the exposed aggregate surface.
- 12 The Contractor shall use a retarder of a type and composition to satisfy the requirements of this Clause.

Application of the Retarder

- 13 The retarder shall be spread evenly on to the surface of the wet concrete slab as soon as practicable after the surface layer has been levelled and finished, by a spray bar over the full width of the slab in one pass. To achieve this uniformity of spread, the spraying system shall consist of a spray bar,

provided with nozzles, mounted on a machine spanning the slab. Temporary works materials and equipment shall be chosen in order to permit inspection to ensure adequate coverage of retarder immediately after spraying and before protection of the surface.

- 14 Before commencing work, the level of the spray bar, the rate of delivery of the retarder from the nozzles of the spray bar, and the forward speed of the spraying machine shall be adjusted to achieve the required rate of spread. Means shall be provided and steps shall be taken to avoid excess retarder flowing on the surface of the slab.
- 15 Back-up spraying equipment shall be available on the Site at all times for use in case of a breakdown of the spraying machine.

Protection of the Surface after the Application of the Retarder

- 16 After application of retarder the Contractor shall protect the finished surface of the pavement concrete against precipitation, moisture loss, contamination and dispersal of the retarder by air movements. This protection shall be applied immediately after the application of the retarder.
- 17 Where waterproof sheeting is used it shall be laid onto the surface of the concrete immediately after the retarder has been sprayed. It shall be retained in position until immediately prior to exposing of the aggregate.
- 18 The protection system shall not adversely affect either the finish, the line or the level of the concrete surface or the even distribution of the retarder in any way. Where sheeting is used, any air bubbling or blistering shall be prevented.

Exposing the Aggregate Surface

- 19 Brushing equipment shall be used to expose the concrete surface aggregate. Where the brushing equipment runs on the slab the concrete shall have gained sufficient strength to avoid any damage to the concrete.
- 20 Removal of the protection system shall take place as brushing proceeds. If waterproof sheeting is used as a protection system it shall be maintained in position until immediately in advance of the brushing operation.
- 21 The Contractor shall complete the process of exposing the aggregate before the retarder becomes ineffective. Failure to do so shall entail the remedial measures specified in sub-Clauses 29 and 30 of this Clause.

Brushing System

- 22 Sufficient brushing capability shall always be maintained on Site to complete the exposure of the aggregate before the retarder becomes ineffective. An adequate back-up brushing facility shall be available on the Site at all times for use in case of a breakdown of the brushing equipment.
- 23 Appropriate brushing equipment shall be used to produce an even macrotexture on the surface of the slab. Brushing shall be carried out in the longitudinal direction of the concrete slab.
- 24 The brushing equipment shall be capable of maintaining an adequate brush rotational speed which in conjunction with the forward working speed is sufficient to remove the surface mortar. Adequate dust suppression and collection measures shall be in operation at all times.

- 25** When complying with the requirements of sub-Clause 19 of this Clause, the wheels of any brushing equipment which may run on the slab shall be fitted with tyres with a shallow tread pattern and a low inflation pressure and be sufficiently wide to avoid damage to the concrete.

Protection of the Surface Layer After Exposure of the Aggregate

- 26** Within one hour of completing exposure of the aggregate the surface shall be dampened with water. A curing compound shall be applied to the entire exposed aggregate surface of the slab in accordance with Clause 1027. In wet weather the curing compound shall be applied as soon as practicable after the rain stops. The surface may, alternatively, be covered by Hessian provided it is maintained in a wet condition at all times during the curing period of the concrete.

Surface Macrottexture Depth and Remedial Measures

- 27** The texture depth of the surface of the concrete shall be measured using a volumetric patch technique described in IS EN 13036-1. The average macrottexture depth of each 1000m section of carriageway lane, or each carriageway lane where less than 1000m, shall comply with the requirements of Appendix 7/1. Any individual result shall be neither greater than the maximum, nor be less than the minimum value of macrottexture depth stated in Appendix 7/1.
- 28** During brushing, initial interim spot check measurements of the surface macrottexture depth shall be made as soon as it is considered that the required texture depth has been reached. This shall continue until the specified macrottexture depth has been achieved.
- 29** In the event that it is not possible to achieve the specified minimum macrottexture depth by further exposure, the Contractor shall treat the surface in accordance with Clause 1029 to achieve the specified macrottexture depth. This treatment shall not be applied until the concrete has reached an age of 28 days and shall not affect the requirements of sub-Clauses 702.2 to 702.4 and 702.5 to 702.9.
- 30** Failure to achieve a satisfactory minimum macrottexture depth by mechanical means shall result in removal of the full thickness of the slab to the extent required to permit reconstruction of the slab in accordance with the Specification. Where the maximum macrottexture depth is exceeded suitable remedial measures shall be employed.

Preliminary Trials

- 31** The Contractor shall carry out preliminary trials to demonstrate to the Employer's Representative, not less than one month prior to the commencement of the trial length referred to in sub-Clauses 37 to 39 of this Clause, the materials, concrete proportions and methods for achieving the macrottexture depth requirements defined in Appendix 7/1.
- 32** Preliminary trial panels shall be constructed off-line incorporating a top surface of exposed aggregate concrete similar to that specified for the permanent works. These panels shall be 20m long and not less than 100mm deep, and the maximum intended paving width. They shall be used to enable the Contractor to determine the required application rate of the retarder and the amount of brushing required in order to achieve the specified macrottexture depth.
- 33** The trial panels may alternatively be constructed on-site, but in this case, they may only form part of the permanent Works if they meet all the requirements of the Specification, otherwise they shall be removed after they have served their purpose.

- 34 The surface macrotexture depth shall be determined by volumetric patch technique at approximately 2m spacings along a diagonal line across each trial panel, and shall follow the procedure described in IS EN 13036-1.
- 35 The average value of each set of 10 individual measurements shall be taken as the resulting macrotexture depth which shall be assessed against the Specification.
- 36 The materials including all the aggregates, plant and equipment used in the preliminary trials shall be equivalent to that which will be used in the Trial Length.

Trial Length

- 37 In addition to the requirements of Clause 1028, the macrotexture depth shall be tested for compliance in accordance with sub-Clauses 38 and 39 of this Clause.
- 38 Macrotexture depth shall be assessed by the volumetric patch technique for each 50m length of the trial length and for each lane, and shall follow the procedure in IS EN 13036-1.
- 39 During the construction of the Trial Length, spot checks shall be made as soon as it is considered that the required macrotexture depth has been reached. Should the texture depth be found to be inadequate, further exposure of the aggregate shall be undertaken until the specified macrotexture depth has been achieved. Where the macrotexture depth is not achieved, and the trial was intended to form part of the running surface of the permanent works, the remedial measures described in sub-Clauses 29 and 30 of this Clause shall apply.

1045 Weather Conditions for Laying of Cementitious Materials

- 1 Road pavement materials in a frozen condition shall not be incorporated in the Works but may be used, if acceptable, when thawed.
- 2 Road pavement materials shall not be laid on any surface which is frozen or covered with ice.
- 3 The temperature of concrete in any pavement layer shall not be less than 5°C at the point of delivery. These materials shall not be laid when the air temperature falls below 3°C and laying shall not be resumed until the rising air temperature reaches 3°C unless all surfaces of the concrete slabs are protected by thermal insulation blankets laid immediately after placing and finishing the concrete. The insulation shall be placed before the temperature of the concrete surface has dropped below 2°C and shall be retained for a minimum of 3 days or until the concrete is assessed to have reached 50% of the specified characteristic compressive strength provided the air temperature is above 0°C and rising at that time. Thermal insulation blankets shall be closed cell polyethylene foam sheets, minimum 10mm thick with a 'U' value of 4 watts/mC (or K value of 0,04 watts/m Kelvin) or suitable material with an equivalent or lower thermal conductivity. They shall be sufficiently robust and capable of being held in place against variations in wind and weather conditions for the necessary curing time.

1046 to 1047 Not Used

1048 Use of Surfaces by Traffic and Construction Plant

- 1 Construction plant and traffic used on pavements under construction shall be suitable in relation to the material, condition and thickness of the courses it traverses so that damage is not caused to the sub-grade or the pavement courses already constructed. The wheels or tracks of plant moving over the various pavement courses shall be kept free from deleterious materials.

- 2 Concrete slabs may be used by traffic when the cube compressive strength is assessed to have reached 25N/mm² for pavement surface slabs, or 20N/mm² for bases with asphalt surfacing. The method of assessing the time when this strength is reached shall be as described in Clause 1004.
- 3 In the absence of test data establishing compliance with sub-Clause 2 of this Clause, no vehicle with an axle loading greater than 2 tonnes shall run on concrete slabs within a period of 14 days after placing the concrete. Vehicles with rubber tyres with an axle loading less than 2 tonnes, or wheels or tracks of concreting plant, shall not use any part of a newly constructed pavement within 7 days. The above periods before traffic may run on the pavement shall be increased if the 7 day cube strength is below that required in the Specification. These periods shall be extended by one day for each night on which the temperature of the layer falls to 0°C or below.



Bonneagar Iompair Éireann
Transport Infrastructure Ireland



Ionad Ghnó Gheata na
Páirce,
Stráid Gheata na Páirce,
Baile Átha Cliath 8, Éire



Parkgate Business Centre,
Parkgate Street,
Dublin 8, Ireland



www.tii.ie



info@tii.ie



+353 (01) 646 3600



+353 (01) 646 3601